



组件 - 塑料
UL 档案号: E187982

CELANESE INTERNATIONAL CORP
SO.F.TER BUSINESS LINE
8040 DIXIE HWY
FLORENCE, KY 41042-2904 United States



Nivioplast B or Nylfor B or CELANYL: R156 GS, B2 HHW GF15
Polyamide 6 (PA6), pellets

可燃性	值	测试方法
UL 阻燃等级		
1.5 mm, ALL	HB	UL 94
3.0 mm, ALL	HB	UL 94
3.0 mm, ALL	HB40	IEC 60695-11-10, -20
1.5 mm, ALL	HB75	IEC 60695-11-10, -20
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746A
1.5 mm	PLC 3	
3.0 mm	PLC 3	
高电弧燃烧指数(HAI)		UL 746A
1.5 mm	PLC 0	
3.0 mm	PLC 0	
相比耐漏电起痕指数(CTI)	PLC 1	UL 746A
高电压电弧起痕速率 (HVTR)	PLC 0	UL 746A
热性能	值	测试方法
RTI Elec		UL 746B
0.75 mm	130 °C	
1.5 mm	130 °C	
3.0 mm	130 °C	
RTI Imp		UL 746B
0.75 mm	100 °C	
1.5 mm	100 °C	
3.0 mm	105 °C	
RTI		UL 746B
0.75 mm	125 °C	
1.5 mm	130 °C	
3.0 mm	130 °C	