

FRIANYL® B3 V0 - PA6
Description

Polyamide 6 compound, unfilled, heat resistant, based on flame retardants halogen and red phosphorous free. UL listed V0@0,38mm
Designed for any electrical application that require self-extinguishing properties, excellent surface quality and flexibility of use.

Physical properties	Value	Unit	Test Standard
Density	72.4	lb/ft ³	ISO 1183
Molding shrinkage, parallel (flow)	1.1 - 1.5	%	ISO 294-4, 2577
Molding shrinkage, transverse normal	1.1 - 1.5	%	ISO 294-4, 2577
Water absorption, 23°C-sat	7.7	%	Sim. to ISO 62
Humidity absorption, 23°C/50%RH	2.3	%	ISO 62
Mechanical properties	Value	Unit	Test Standard
Tensile modulus	543892/-	psi	ISO 527-1, -2
Tensile stress at yield, 50mm/min	10900/-	psi	ISO 527-1, -2
Tensile strain at break, 50mm/min	7/-	%	ISO 527-1, -2
Charpy impact strength, 23°C	22.8/-	ft-lb/in ²	ISO 179/1eU
Charpy notched impact strength, 23°C	1.43/-	ft-lb/in ²	ISO 179/1eA
Ball indentation hardness, 30s	20300	psi	ISO 2039-1
Thermal properties	Value	Unit	Test Standard
Melting temperature, 20°C/min	437	°F	ISO 11357-1/-3
DTUL at 1.8 MPa	158	°F	ISO 75-1, -2
DTUL at 0.45 MPa	356	°F	ISO 75-1, -2
FMVSS	SE	-	ISO 3795 (FMVSS 302)
Flammability @3.2mm nom. thickn.	V-0	class	UL 94
Flammability @0.4mm nom. thickn.	V-0	class	UL 94
Glow wire flammability index, 0.4 mm	1760	°F	IEC 60695-2-12
Glow wire flammability index, 3.2 mm	1760	°F	IEC 60695-2-12
Ball pressure test	392	°F	IEC 60695-10-2
RTI - electrical @ 0.4mm nom. Thickn.	125	°C	UL 746B
RTI - electrical @ 0.8mm nom. Thickn.	125	°C	UL 746B
RTI - electrical @ 1.6mm nom. Thickn.	125	°C	UL 746B
RTI - electrical @ 3.2mm nom. Thickn.	125	°C	UL 746B
RTI - impact @ 0.4mm nom. Thickn.	90	°C	UL 746B
RTI - impact @ 0.8mm nom. Thickn.	90	°C	UL 746B
RTI - impact @ 1.6mm nom. Thickn.	95	°C	UL 746B
RTI - impact @ 3.2mm nom. Thickn.	95	°C	UL 746B
RTI - str @ 0.4mm nom. Thickn.	115	°C	UL 746B
RTI - str @ 0.8mm nom. Thickn.	115	°C	UL 746B
RTI - str @ 1.6mm nom. Thickn.	115	°C	UL 746B
RTI - str @ 3.2mm nom. Thickn.	115	°C	UL 746B
Electrical properties	Value	Unit	Test Standard
Comparative tracking index	PLC 1/-	-	UL 746
Comparative tracking index	Group I	-	IEC 60112
CTI 50 drops	600	V	IEC 60112
Hot wire ignition @ 0.8mm nom. thickn.	PLC 4	class	UL 746A
Hot wire ignition @ 1.6mm nom. thickn.	PLC 3	class	UL 746A
Hot wire ignition @ 3.2mm nom. thickn.	PLC 2	class	UL 746A
High ampere arc ignition @ 0.8mm nom. thickn.	PLC 0	class	UL 746A
High ampere arc ignition @ 1.6mm nom. thickn.	PLC 0	class	UL 746A
High ampere arc ignition @ 3.2mm nom. thickn.	PLC 0	class	UL 746A

FRIANYL® B3 V0 - PA6

VDA Properties

	Value	Unit
FMVSS	SE	ISO 3795 (FMVSS 302)

Other text information

Injection Molding Preprocessing

PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection molding process should be lower than 0.15%, according to the grade and to the molded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically, 4-8 hours at 80-90 °C using dehumidified air (dew point of -20 °C) are suitable conditions for a starting moisture content of 0.20%-0.40%.

Injection molding

The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290 °C (PA66), 235-270 °C (PA6), nozzle and hot runners up to 300 °C (up to 290 °C products with flame retardants). Mold temperatures: 60-80 °C, (80-100 °C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300 °C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.

Injection Molding Postprocessing

PA materials reach their final performance with a water content of about 1.5 to 3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After molding, in favorable environmental conditions, a part can quickly absorb moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A conditioning treatment can accelerate further the initial water absorption of the molded parts. Conditioning is usually carried out in hot and humid environment (for example 50 °C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be considered, especially in unfilled grades. Post-treatments of parts may also include the annealing (60-80 °C in oven, up to four hours). This procedure can be useful to relax any internal stresses.

Characteristics

Special Characteristics	Auto spec approved, Flame retardant, Heat resistant
Processing	Injection molding

FRIANYL® B3 V0 - PA6

responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products. The products mentioned herein are not intended for use in medical or dental implants.

Trademark

© 2022 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.