

Starflam® PX08029I

polyamide 6



Starflam PX08029I is a 20% glass filled, flame retardant PA6 for injection molded applications. The material is halogen free and red phosphorus free.

General

Regional Availability	• North America	• Europe
Additive	• Flame Retarding Agent	• Heat Stabilizer
Features	• Flame Retardant	
Agency Rating	• ISO, 1043 PA6 GF20 FR(30)	
Appearance	• Natural Color	
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical

	dry	cond.	Unit	Test Standard
Density	1.36	-	g/cm ³	ISO 1183

Mechanical

	dry	cond.	Unit	Test Standard
Tensile Stress (Yield, 23°C)	91	-	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.3	-	%	ISO 527-2
Flexural Modulus (23°C)	4800	-	MPa	ISO 178
Flexural Strength (23°C)	122	-	MPa	ISO 178

Impact

	dry	cond.	Unit	Test Standard
Notched Izod Impact Strength, +23°C	3.6	-	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength, +23°C	25	-	kJ/m ²	ISO 180/1U

Thermal

	dry	cond.	Unit	Test Standard
Heat Deflection Temperature, 1.80 MPa, Unannealed	166	-	°C	ISO 75-2/A

Injection

	Value	Unit
Drying Temperature	80	°C
Drying Time	4	h
Suggested Max Moisture	0.2	%
Rear Temperature	240 - 250	°C
Middle Temperature	250 - 260	°C
Front Temperature	250 - 270	°C
Processing (Melt) Temperature	250 - 270	°C

+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)

Starflam® PX08029I

polyamide 6



Mold Temperature

50 - 90

°C

