

Vydyne® B BK X146 EM2 LT K1

polyamide 6



Vydyne B BK X146 EM2 LT K1 is a general-purpose, impact-modified PA6 resin. Available in black, it is inorganic heat-stabilized for improved resistance to high temperatures. It is lubricated for machine feed and easy mold release and shows a high impact resistance also at low temperatures.

General

Regional Availability	• North America	• Europe	• Asia Pacific
Additive	• Heat Stabilizer	• Lubricant	
Features	• Abrasion Resistance • Good Mold Release • High Elongation • Oil Resistant	• Chemical Resistant • Good Toughness • Low Temperature Impact Resistance • Solvent Resistant	• Gasoline Resistant • Heat Aging Resistant • Lubricated
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical

	dry	cond.	Unit	Test Standard
Density	1.10	-	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	1.9	*	%	
Flow : 23°C, 2.00 mm	1.6	*	%	
Water Absorption				ISO 62
Equilibrium, 23°C, 50% RH	2.5	*	%	

Mechanical

	dry	cond.	Unit	Test Standard
Tensile Modulus (23°C)	2400	1600	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	62	40	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	6	10	%	ISO 527-2
Tensile Strain (Break, 23°C)	55	65	%	ISO 527-2

Impact

	dry	cond.	Unit	Test Standard
Notched Izod Impact Strength				ISO 180/1A
+23°C	20	-	kJ/m ²	
-30°C	12	-	kJ/m ²	

Thermal

	dry	cond.	Unit	Test Standard
Heat Deflection Temperature				ISO 75-2/A
1.80 MPa, Unannealed	60	-	°C	
0.45 MPa, Unannealed	145	-	°C	

Vydyne® B BK X146 EM2 LT K1

polyamide 6



Melting Temperature	222	*	°C	ISO 11357-3
---------------------	-----	---	----	-------------

Electrical	Value	Unit	Test Standard
------------	-------	------	---------------

Comparative Tracking Index (3.00 mm)	450	V	IEC 60112
--------------------------------------	-----	---	-----------

Flammability	Value	Test Standard
--------------	-------	---------------

Flammability		UL 94
0.750 mm	HB	
1.50 mm	HB	

Injection	Value	Unit
-----------	-------	------

Drying Temperature	80 - 90	°C
Drying Time	≥ 3	h
Rear Temperature	230 - 270	°C
Middle Temperature	230 - 270	°C
Front Temperature	230 - 270	°C
Nozzle temperature	230 - 270	°C
Processing (Melt) Temperature	230 - 270	°C
Mold Temperature	80 - 90	°C

