

Starflam® 525K BK0778

polyamide 66

Starflam 525K BK0778 (formerly Vydyn® ECO525K BK0778) is a non-halogenated flame retardant, PA66 grade modified with 25% glass fiber for improved stiffness and strength.

General

Regional Availability	• North America	• Europe	• Asia Pacific
Additive	• Flame Retarding Agent		
Features	• Corrosion Resistant	• Fast Molding Cycle	• Flame Retardant
	• Good Dimensional Stability	• Good Processability	• Heat Aging Resistant
	• High Flow	• High Strength	• Low Density
Automotive Specifications	• Tesla TM-1006-303120V (compliance)		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical

	dry	cond.	Unit	Test Standard
Density	1.40	-	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	1.1	*	%	
Flow : 23°C, 2.00 mm	0.3	*	%	
Water Absorption				ISO 62
23°C, 24 hr	1.2	*	%	
Equilibrium, 23°C, 50% RH	1.9	*	%	

Mechanical

	dry	cond.	Unit	Test Standard
Tensile Modulus (23°C)	8500	6900	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	127	91	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.7	3	%	ISO 527-2
Flexural Modulus (23°C)	9100	5900	MPa	ISO 178
Flexural Strength (23°C)	193	127	MPa	ISO 178

Impact

	dry	cond.	Unit	Test Standard
Charpy Notched Impact Strength				ISO 179/1eA
+23°C	8.9	11	kJ/m ²	
-30°C	8.3	7.6	kJ/m ²	
-40°C	8.3	7.9	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
+23°C	57	62	kJ/m ²	

Starflam® 525K BK0778

polyamide 66

-30°C	57	53	kJ/m²	
-40°C	55	53	kJ/m²	
Notched Izod Impact Strength				ISO 180/1A
+23°C	8.1	10	kJ/m²	
-30°C	7.8	7.9	kJ/m²	
-40°C	7.7	7.7	kJ/m²	

Thermal	dry	cond.	Unit	Test Standard
Heat Deflection Temperature				ISO 75-2/A
1.80 MPa, Unannealed	237	228	°C	
0.45 MPa, Unannealed	256	254	°C	
Melting Temperature	260	*	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C, 2.00 mm	23	*	E-6/K	
Transverse : 23 to 55°C, 2.00 mm	67	*	E-6/K	
RTI Elec				UL 746
0.200 mm	140		°C	
0.400 mm	140		°C	
0.750 mm	140		°C	
1.50 mm	140		°C	
3.00 mm	140		°C	
RTI Imp				UL 746
0.200 mm	95		°C	
0.400 mm	110		°C	
0.750 mm	120		°C	
1.50mm	130		°C	
3.00 mm	130		°C	
RTI Str				UL 746
0.200 mm	115		°C	
0.400 mm	130		°C	
0.750 mm	140		°C	
1.50 mm	150		°C	
3.00 mm	150		°C	

Electrical	dry	cond.	Unit	Test Standard
Dielectric Strength (1.00 mm)	42	-	kV/mm	IEC 60243
Comparative Tracking Index (3.00 mm)	600		V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.400 mm	PLC 0		-	
0.750 mm	PLC 0		-	

Starflam® 525K BK0778

polyamide 66



1.50 mm	PLC 0	-
3.00 mm	PLC 0	-
Hot-wire Ignition (HWI)		UL 746
0.400 mm	PLC 2	-
0.750 mm	PLC 1	-
1.50 mm	PLC 0	-
3.00 mm	PLC 0	-

Flammability	Value	Unit	Test Standard
Flammability			UL 94
0.200 mm	V-0	-	
0.400 mm	V-0	-	
0.750 mm	V-0	-	
1.50 mm	V-0	-	
3.00 mm	V-0	-	
Flammability, 5V			UL 94
1.50 mm	5VA	-	
3.00 mm	5VA	-	
Glow Wire Flammability Index			IEC 60695-2-12
0.200 mm	960	°C	
0.400 mm	960	°C	
0.750 mm	960	°C	
1.50 mm	960	°C	
3.00 mm	960	°C	

Injection	Value	Unit
Drying Temperature	80	°C
Drying Time	4 - 6	h
Rear Temperature	275 - 300	°C
Middle Temperature	275 - 300	°C
Front Temperature	275 - 300	°C
Processing (Melt) Temperature	275 - 300	°C
Mold Temperature	60 - 120	°C

