

Vydyne® 47H NT0688

polyamide 66



Vydyne 47H NT0688 is general-purpose, medium impact-modified, heat stabilized PA66 resin. The product offers improved resistance to thermal degradation.

47H NT0688 is recognized for all the processing and property advantages inherent to PA66 with the addition of improved impact strength. This resin offers a well balanced combination of engineering properties characterized by high melt point, good surface lubricity, abrasion resistance and resistance to many chemicals, machine and motor oils, solvents and gasoline.

General

Regional Availability	• North America	• Europe	• Asia Pacific
Additive	• Heat Stabilizer		
Features	• Abrasion Resistance • General Purpose • Heat Stabilized • Low Temperature Toughness	• Chemical Resistant • Good Processability • High Impact Resistance • Oil Resistant	• Gasoline Resistant • Good Toughness • Low Temperature Impact Resistance • Solvent Resistant
Agency Rating	• ASTM, D4066 PA0161	• ASTM, D6779 PA0161	• SAE, J1639 PA0171
Automotive Specifications	• Chery Q-SQR.S1-33-2012 CMP.PA66.A2	• Daimler DBL 5410 (compliance)	• GM GMW16447P-PA66-T2
UL File Number	• E70062		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical

	dry	cond.	Unit	Test Standard
Density	1.10	-	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	1.6	*	%	
Flow : 23°C, 2.00 mm	1.8	*	%	
Water Absorption				ISO 62
23°C, 24 hr	1.2	*	%	
Equilibrium, 23°C, 50% RH	2.3	*	%	

Mechanical

	dry	cond.	Unit	Test Standard
Tensile Modulus (23°C)	2800	1700	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	60	45	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	52	40	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	22	60	%	ISO 527-2
Flexural Modulus (23°C)	2300	800	MPa	ISO 178

Vydyne® 47H NT0688

polyamide 66



Flexural Strength (23°C)	70	24	MPa	ISO 178
Impact	dry	cond.	Unit	Test Standard
Charpy Notched Impact Strength				ISO 179/1eA
+23°C	19	62	kJ/m²	
-30°C	17	24	kJ/m²	
-40°C	11	18	kJ/m²	
Charpy Unnotched Impact Strength				ISO 179/1eU
+23°C	N	N	kJ/m²	
-30°C	N	N	kJ/m²	
Notched Izod Impact Strength				ISO 180/1A
+23°C	18	44	kJ/m²	
-30°C	16	24	kJ/m²	
-40°C	12	18	kJ/m²	
Thermal	dry	cond.	Unit	Test Standard
Heat Deflection Temperature				ISO 75-2/A
1.80 MPa, Unannealed	63	-	°C	
0.45 MPa, Unannealed	185	-	°C	
Melting Temperature	260	*	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C, 2.00 mm	110	*	E-6/K	
Transverse : 23 to 55°C, 2.00 mm	140	*	E-6/K	
RTI Elec				UL 746
0.750 mm	130		°C	
1.50 mm	130		°C	
3.00 mm	130		°C	
RTI Imp				UL 746
0.750 mm	75		°C	
1.50mm	75		°C	
3.00 mm	75		°C	
RTI Str				UL 746
0.750 mm	115		°C	
1.50 mm	115		°C	
3.00 mm	115		°C	

Vydyne® 47H NT0688

polyamide 66



Electrical	dry	cond.	Unit	Test Standard
Volume Resistivity (1.00 mm)	1E9	-	Ohm*m	IEC 60093
Dielectric Strength (1.00 mm)	12	-	kV/mm	IEC 60243
Arc Resistance (3.00 mm)	6	-	-	ASTM D 495
Comparative Tracking Index (3.00 mm)	525	-	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.750 mm	PLC 0	-	-	
1.50 mm	PLC 0	-	-	
3.00 mm	PLC 0	-	-	
High Voltage Arc Tracking Rate (HVTR), 3.00 mm	PLC 2	-	-	UL 746
Hot-wire Ignition (HWI)				UL 746
0.750 mm	PLC 4	-	-	
1.50 mm	PLC 4	-	-	
3.00 mm	PLC 3	-	-	

Flammability	Value	Unit	Test Standard
Flammability			UL 94
0.750 mm	HB	-	
1.50 mm	HB	-	
3.00 mm	HB	-	
Glow Wire Flammability Index			IEC 60695-2-12
0.750 mm	700	°C	
1.50 mm	775	°C	
3.00 mm	700	°C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.750 mm	725	°C	
1.50 mm	800	°C	
3.00 mm	725	°C	

Injection	Value	Unit
Drying Temperature	80	°C
Drying Time	4	h
Rear Temperature	280 - 310	°C
Middle Temperature	280 - 310	°C
Front Temperature	280 - 310	°C
Nozzle temperature	280 - 310	°C
Processing (Melt) Temperature	285 - 305	°C
Mold Temperature	65 - 95	°C

