

Vydyne® LUB A 30 FC BK TF3

polyamide 66



Vydyne LUB A 30 FC BK TF3 is standard flow 30% carbon-fiber reinforced, 15% PTFE lubricated PA66 resin. Available in black, it is specifically designed for high stiffness and strength. This product also has a low coefficient of friction and is electrically conductive.

General

Regional Availability	• North America	• Europe	• Asia Pacific
Additive	• Lubricant		
Features	• Abrasion Resistance • General Purpose • High Tensile Strength	• Chemical Resistant • Good Flow • Lubricated	• Gasoline Resistant • Good Stiffness • Slip
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical

	dry	cond.	Unit	Test Standard
Density	1.39	-	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	0.4	*	%	
Flow : 23°C, 2.00 mm	0.1	*	%	
Water Absorption				ISO 62
Equilibrium, 23°C, 50% RH	1.7	*	%	

Mechanical

	dry	cond.	Unit	Test Standard
Tensile Modulus (23°C)	19500	14400	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	215	170	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	1.5	3	%	ISO 527-2

Impact

	dry	cond.	Unit	Test Standard
Notched Izod Impact Strength, +23°C	8	11	kJ/m ²	ISO 180/1A

Thermal

	dry	cond.	Unit	Test Standard
Heat Deflection Temperature				ISO 75-2/A
1.80 MPa, Unannealed	245	-	°C	
0.45 MPa, Unannealed	250	-	°C	
Melting Temperature	260	*	°C	ISO 11357-3

Vydyne® LUB A 30 FC BK TF3

polyamide 66



Electrical	dry	cond.	Unit	Test Standard
Volume Resistivity (1.00 mm)	100	-	Ohm*m	IEC 60093

Flammability	Value	Test Standard
Flammability		UL 94
1.50 mm	HB	
3.00 mm	HB	

Injection	Value	Unit
Drying Temperature	90 - 110	°C
Drying Time	≥ 3	h
Rear Temperature	270 - 280	°C
Middle Temperature	270 - 295	°C
Front Temperature	270 - 295	°C
Nozzle temperature	270 - 295	°C
Processing (Melt) Temperature	270 - 295	°C
Mold Temperature	70 - 90	°C

