

# Vydyne® R550HC

polyamide 66



Vydyne R550HC is a general purpose, 50% glass-filled, heat-stabilized PA66 based resin designed for injection molding applications. R550HC offers standard flow with a natural surface finish and maintains the excellent resistance typical of PA66 in chemicals, machine and motor oils, solvents, and gasoline.

## General

|                       |                                                        |                                                       |                                        |
|-----------------------|--------------------------------------------------------|-------------------------------------------------------|----------------------------------------|
| Regional Availability | • North America                                        | • Europe                                              | • Asia Pacific                         |
| Additive              | • Heat Stabilizer                                      | • Lubricant                                           |                                        |
| Features              | • Creep Resistant<br>• Heat Stabilized<br>• Lubricated | • Good Flow<br>• High Rigidity<br>• Thermal Stability | • Good Mold Release<br>• High Strength |
| Agency Rating         | • ASTM, D6779 PA012G50<br>• EU, 2023/2006              | • EC, 1935/2004<br>• FDA, 21 CFR 177.1500             | • EU, 10/2011                          |
| UL File Number        | • E70062                                               |                                                       |                                        |
| Appearance            | • Natural Color                                        |                                                       |                                        |
| Forms                 | • Pellets                                              |                                                       |                                        |
| Processing Method     | • Injection Molding                                    |                                                       |                                        |

## Physical

|                             | dry  | cond. | Unit              | Test Standard |
|-----------------------------|------|-------|-------------------|---------------|
| Density                     | 1.58 | -     | g/cm <sup>3</sup> | ISO 1183      |
| Molding Shrinkage           |      |       |                   | ISO 294-4     |
| Across Flow : 23°C, 2.00 mm | 0.8  | *     | %                 |               |
| Flow : 23°C, 2.00 mm        | 0.3  | *     | %                 |               |
| Water Absorption            |      |       |                   | ISO 62        |
| 23°C, 24 hr                 | 0.5  | *     | %                 |               |
| Equilibrium, 23°C, 50% RH   | 1.2  | *     | %                 |               |

## Mechanical

|                              | dry   | cond. | Unit | Test Standard |
|------------------------------|-------|-------|------|---------------|
| Tensile Modulus (23°C)       | 16800 | 12600 | MPa  | ISO 527-2     |
| Tensile Stress (Break, 23°C) | 240   | 180   | MPa  | ISO 527-2     |
| Tensile Strain (Break, 23°C) | 2.5   | 3.5   | %    | ISO 527-2     |
| Flexural Modulus (23°C)      | 16000 | 11200 | MPa  | ISO 178       |
| Flexural Strength (23°C)     | 350   | 270   | MPa  | ISO 178       |
| Poisson's Ratio (23°C)       | 0.4   | -     |      | ISO 527-2     |

## Impact

|                                | dry | cond. | Unit              | Test Standard |
|--------------------------------|-----|-------|-------------------|---------------|
| Charpy Notched Impact Strength |     |       |                   | ISO 179/1eA   |
| +23°C                          | 15  | 21    | kJ/m <sup>2</sup> |               |
| -30°C                          | 14  | 15    | kJ/m <sup>2</sup> |               |

# Vydyne® R550HC

polyamide 66



|                                  |    |     |                   |             |
|----------------------------------|----|-----|-------------------|-------------|
| Charpy Unnotched Impact Strength |    |     |                   | ISO 179/1eU |
| +23°C                            | 95 | 110 | kJ/m <sup>2</sup> |             |
| -30°C                            | 91 | 95  | kJ/m <sup>2</sup> |             |

|                              |    |    |                   |            |
|------------------------------|----|----|-------------------|------------|
| Notched Izod Impact Strength |    |    |                   | ISO 180/1A |
| +23°C                        | 17 | 21 | kJ/m <sup>2</sup> |            |
| -30°C                        | 16 | 18 | kJ/m <sup>2</sup> |            |

| Thermal                          | dry | cond. | Unit  | Test Standard |
|----------------------------------|-----|-------|-------|---------------|
| Heat Deflection Temperature      |     |       |       | ISO 75-2/A    |
| 1.80 MPa, Unannealed             | 255 | -     | °C    |               |
| 0.45 MPa, Unannealed             | 260 | -     | °C    |               |
| Melting Temperature              | 260 | *     | °C    | ISO 11357-3   |
| CLTE                             |     |       |       | ISO 11359-2   |
| Flow : 23 to 55°C, 2.00 mm       | 12  | *     | E-6/K |               |
| Transverse : 23 to 55°C, 2.00 mm | 100 | *     | E-6/K |               |
| RTI Elec                         |     |       |       | UL 746        |
| 0.750 mm                         | 140 |       | °C    |               |
| 1.50 mm                          | 140 |       | °C    |               |
| 3.00 mm                          | 140 |       | °C    |               |
| RTI Imp                          |     |       |       | UL 746        |
| 0.750 mm                         | 130 |       | °C    |               |
| 1.50mm                           | 130 |       | °C    |               |
| 3.00 mm                          | 130 |       | °C    |               |
| RTI Str                          |     |       |       | UL 746        |
| 0.750 mm                         | 140 |       | °C    |               |
| 1.50 mm                          | 140 |       | °C    |               |
| 3.00 mm                          | 140 |       | °C    |               |

| Electrical                                     | dry       | cond. | Unit  | Test Standard |
|------------------------------------------------|-----------|-------|-------|---------------|
| Volume Resistivity (1.00 mm)                   | 1E10      | -     | Ohm*m | IEC 60093     |
| Dielectric Strength (1.00 mm)                  | 20        | -     | kV/mm | IEC 60243     |
| Arc Resistance (3.00 mm)                       | 5         |       | -     | ASTM D 495    |
| Comparative Tracking Index (3.00 mm)           | 400 - 599 |       | V     | IEC 60112     |
| High Amp Arc Ignition (HAI)                    |           |       |       | UL 746        |
| 0.750 mm                                       | PLC 0     |       | -     |               |
| 1.50 mm                                        | PLC 0     |       | -     |               |
| 3.00 mm                                        | PLC 0     |       | -     |               |
| High Voltage Arc Tracking Rate (HVTR), 3.00 mm | PLC 1     |       | -     | UL 746        |
| Hot-wire Ignition (HWI)                        |           |       |       | UL 746        |

# Vydyne® R550HC

polyamide 66



|          |       |   |
|----------|-------|---|
| 0.750 mm | PLC 4 | - |
| 1.50 mm  | PLC 3 | - |
| 3.00 mm  | PLC 4 | - |

| Flammability                   | Value | Unit   | Test Standard  |
|--------------------------------|-------|--------|----------------|
| Burning Rate, 2.00 mm          |       | mm/min | ISO 3795       |
| Flammability                   |       |        | UL 94          |
| 0.750 mm                       | HB    | -      |                |
| 1.50 mm                        | HB    | -      |                |
| 3.00 mm                        | HB    | -      |                |
| Glow Wire Flammability Index   |       |        | IEC 60695-2-12 |
| 0.750 mm                       | 675   | °C     |                |
| 1.50 mm                        | 675   | °C     |                |
| 3.00 mm                        | 960   | °C     |                |
| Glow Wire Ignition Temperature |       |        | IEC 60695-2-13 |
| 0.750 mm                       | 700   | °C     |                |
| 1.50 mm                        | 700   | °C     |                |
| 3.00 mm                        | 750   | °C     |                |

| Injection                     | Value     | Unit |
|-------------------------------|-----------|------|
| Drying Temperature            | 80        | °C   |
| Drying Time                   | 4         | h    |
| Rear Temperature              | 280 - 310 | °C   |
| Middle Temperature            | 280 - 310 | °C   |
| Front Temperature             | 280 - 310 | °C   |
| Nozzle temperature            | 280 - 310 | °C   |
| Processing (Melt) Temperature | 285 - 305 | °C   |
| Mold Temperature              | 65 - 95   | °C   |

