

Ultramid® 8254 HS BK-102

Polyamide 6



Product Description

Ultramid 8254 HS BK-102 is a highly flexible, heat stabilized, pigmented black, impact modified PA6 extrusion compound for tubing application.

Applications

Ultramid 8254 HS BK-102 is generally recommended for applications such as convoluted and emission tubing, cable jacketing and other types of automotive tubing.

PHYSICAL	ASTM Test Method	Property Value	
Specific Gravity	D-792	1.07	
Mold Shrinkage (1/8" bar, in/in)		0.013	
Moisture, %	D-570		
(24 Hour)		1.2	
(50% RH)		2	
(Saturation)		7.1	
MECHANICAL	ASTM Test Method	Dry	Conditioned
Tensile Strength, Yield, MPa (psi)	D-638		
-40C (-40F)		83 (12,000)	104 (15,100)
23C (73F)		34 (4,930)	26 (3,770)
80C (176F)		15 (2,170)	-
121C (250F)		12 (1,740)	-
Elongation, Yield, %	D-638		
23C (73F)		30	-
Elongation, Break, %	D-638		
23C (73F)		>100	-
Flexural Modulus, MPa (psi)	D-790		
23C (73F)		610 (88,400)	-
Flexural Strength, MPa (psi)	D-790		
23C (73F)		28 (4,060)	-
Rockwell Hardness, R Scale	D-785	40	-
IMPACT	ASTM Test Method	Dry	Conditioned
Notched Izod Impact, J/M (ft-lbs/in)	D-256		
23C (73F)		640 (12.0)	-
THERMAL	ASTM Test Method	Dry	Conditioned
Melting Point, C(F)	D-3418	220 (428)	-
Heat Deflection @ 264 psi (1.8 MPa) C(F)	D-648	47 (116)	-
Heat Deflection @ 66 psi (.45 MPa) C(F)	D-648	124 (255)	-
Coef. of Linear Thermal Expansion, mm/mm C (in/in F)	E-831	1.17 X10-4	-
UL RATINGS	UL Test Method	Property Value	
Flammability Rating, 1.5mm	UL94	HB	
Relative Temperature Index, 1.5mm	UL746B		
Mechanical w/o Impact, C		65	



BASF Corporation
Engineering Plastics
609 Biddle Avenue
Ypsilanti, MI 48192



Ultramid® 8254 HS BK-102



Mechanical w/ Impact, C	65		
Electrical, C	65		
ELECTRICAL	ASTM Test Method	Dry	Conditioned
Volume Resistivity, 1.5 mm	D-257	>1E13	-

Processing Guidelines

Material Handling

Max. Water content: 0.1%

Product is supplied in sealed containers and drying prior to molding is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 65 degC (149 degF) is recommended. Drying time is dependent on moisture level, but 2-4 hours is generally sufficient. Further information concerning safe handling procedures can be obtained from the Material Safety Data Sheet. Alternatively, please contact your BASF representative.

Typical Profile

Melt Temperature 240-250 degC (464-482 degF)

Typical Barrel Profile (degC):

Rear 245-255 degC (473-491 degF)
Middle 245-260 degC (473-500 degF)
Front 240-250 degC (464-482 degF)

Head 230-245 degC (446-473 degF)
Flange 230-245 degC (446-473 degF)
Die 230-245 degC (446-473 degF)

Screw Parameters

Metering Section	40%
Transition Section	3 to 4 flights
Feed Section	balance of screw length
Compression Ratio	3.5:1 to 4.0:1
L/D Ratio	20:1 to 24:1

Tooling & Sizing

Die to Finished Tube dia. 1.5-2.0:1

Selection of pin and die size will be dependent on the material viscosity. In general, the ratio of die size to finished tube diameter is about 1.5-2.0:1. The mandrel (pin) size is determined the same way in relation to the inner tube diameter.

Free (open tank) extrusion is recommended when producing tube diameters 9.5mm and below. For larger diameters, a differential pressure vacuum tank is recommended.

Tooling draw ratio is generally higher with free extrusion versus sizing, but will depend on melt viscosity. The vacuum sizer entrance should be about 3-9% larger than the finished tube outer diameter. Selection will depend on melt viscosity and die swell of the extrudate.



BASF Corporation
Engineering Plastics
609 Biddle Avenue
Yandotte, MI 48192



Quenching

For diameters less than or equal to 9.5mm (.37") O.D., open tank quenching with normal tap water is suggested. Depending upon line speed, quenching distance can vary from 7.5 to 12 meters (24.6 -39.4 feet). A short air gap (die to quench water) is recommended for both tubing and cable jacketing for best flexibility.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.



BASF Corporation
Engineering Plastics
609 Biddle Avenue
Yandotte, MI 48192

