

Ultramid® 8351 HS BK-102

Polyamide 6



Product Description

Ultramid 8351 HS BK-102 is a heat stabilized, pigmented black, impact modified type 6 nylon graft copolymer developed for injection molding applications requiring a high level of toughness combined with a moderate flexibility and faster cycles. Excellent thermal and chemical resistance properties provided by the nylon backbone. It demonstrates the highest impact performance within the Ultramid copolymer product line while maintaining an excellent balance of strength and stiffness. Excellent chemical resistance to greases, oils and hydrocarbons.

Applications

Ultramid 8351 HS BK-102 is generally recommended for applications such as spray gun and power tool handles, trim clips and fasteners, wall anchors and automotive roof clips/rack components.

PHYSICAL	ASTM Test Method	Property Value	
Specific Gravity	D-792	1.07	
Mold Shrinkage (1/8" bar, in/in)		0.014	
Moisture, %	D-570		
(24 Hour)		1.1	
(50% RH)		1.9	
(Saturation)		6.7	
MECHANICAL	ASTM Test Method	Dry	Conditioned
Tensile Strength, Yield, MPa (psi)	D-638		
23C (73F)		55 (7,970)	-
Elongation, Yield, %	D-638		
23C (73F)		5	-
Elongation, Break, %	D-638		
23C (73F)		>100	-
Flexural Modulus, MPa (psi)	D-790		
23C (73F)		1,690 (245,000)	-
Flexural Strength, MPa (psi)	D-790		
23C (73F)		66 (9,570)	-
Rockwell Hardness, R Scale	D-785	78	-
IMPACT	ASTM Test Method	Dry	Conditioned
Notched Izod Impact, J/M (ft-lbs/in)	D-256		
23C (73F)		NB	-
Drop Weight Impact, ft-lbs, 23C	BASF Drop Weight Impact Test	210	-
THERMAL	ASTM Test Method	Dry	Conditioned
Melting Point, C(F)	D-3418	220 (428)	-
Heat Deflection @ 264 psi (1.8 MPa) C(F)	D-648	55 (131)	-
Coef. of Linear Thermal Expansion, mm/mm C (in/in F)	E-831	1.06 X10-4	-
UL RATINGS	UL Test Method	Property Value	
Flammability Rating, 1.5mm	UL94	HB	
Relative Temperature Index, 1.5mm	UL746B		



BASF Corporation
Engineering Plastics
609 Biddle Avenue
Ypsilanti, MI 48192



Ultramid® 8351 HS BK-102

BASF
The Chemical Company

Mechanical w/o Impact, C	105		
Mechanical w/ Impact, C	105		
Electrical, C	105		
ELECTRICAL	ASTM Test Method	Dry	Conditioned
Volume Resistivity, 1.5 mm	D-257	>1E13	-

Processing Guidelines

Material Handling

Max. Water content: 0.2%

Product is supplied in sealed containers and drying prior to molding is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 80 degC (176 degF) is recommended. Drying time is dependent on moisture level, but 2-4 hours is generally sufficient. Further information concerning safe handling procedures can be obtained from the Material Safety Data Sheet. Alternatively, please contact your BASF representative.

Typical Profile

Melt Temperature 240-270 degC (464-518 degF)

Mold Temperature 80-95 degC (176-203 degF)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

Mold Temperatures

A mold temperature of 80-95 degC (176-203 degF) is recommended, but temperatures of 10-95 degC (50-203 degF) can be used where applicable.

Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.



BASF Corporation
Engineering Plastics
609 Biddle Avenue
Yandotte, MI 48192

