

Ultramid® B3WG6

Polyamide 6



Product Description

Ultramid B3WG6 is a 30% glass fiber reinforced, heat stabilized injection molding PA6 grade.


Applications

Typical applications include automotive manifolds and pedals.

PHYSICAL		ASTM Test Method	Property Value	
Specific Gravity		D-792	1.36	
Mold Shrinkage (1/8" bar, in/in)			0.003	
Moisture, %		D-570		
(50% RH)			2.1	
(Saturation)			6.6	
MECHANICAL		ASTM Test Method	Dry	Conditioned
Tensile Strength, Break, MPa (psi)		D-638		
23C (73F)			179 (26,000)	-
Elongation, Break, %		D-638		
23C (73F)			3.3	-
Flexural Modulus, MPa (psi)		D-790		
23C (73F)			8,280 (1,200,000)	-
IMPACT		ASTM Test Method	Dry	Conditioned
Notched Izod Impact, J/M (ft-lbs/in)		D-256		
-40C (-40F)			107 (2.0)	-
23C (73F)			134 (2.5)	-
THERMAL		ASTM Test Method	Dry	Conditioned
Melting Point, C(F)		D-3418	220 (428)	-
Heat Deflection @ 264 psi (1.8 MPa) C(F)		D-648	207 (404)	-
Heat Deflection @ 66 psi (.45 MPa) C(F)		D-648	220 (428)	-
Coef. of Linear Thermal Expansion, mm/mm C (in/in F)		E-831	0.1 X10 ⁻⁴	-
UL RATINGS		UL Test Method	Property Value	
Flammability Rating, 1.5mm		UL94	HB	
Relative Temperature Index, 1.5mm		UL746B		
Mechanical w/o Impact, C			130	
Mechanical w/ Impact, C			90	
Electrical, C			130	
ELECTRICAL		ASTM Test Method	Dry	Conditioned
Volume Resistivity, 1.5 mm		D-257	1E13	1E10

Processing Guidelines

Material Handling



BASF Corporation
Engineering Plastics
609 Biddle Avenue
Yandotte, MI 48192

Material is supplied in sealed containers and drying prior to molding in a dehumidifying or desiccant dryer is recommended. Drying parameters are dependent upon the actual percentage of moisture in the pellets and typical pre-drying conditions are 2-4 hours at 180F (83C). Recommended moisture levels for achieving optimum surface qualities and mechanical properties is 0.05% - 0.12%. Further information concerning safe handling procedures can be obtained from the Material Safety Data Sheet (MSDS), or by contacting your BASF representative.

Typical Profile

Melt Temperature 270-295 degC (518-563 degF)
Mold Temperature 80-95 degC (176-203 degF)
Injection and Packing Pressure 35-125 bar (500-1500 psi)

Mold Temperatures

This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics are critical, a mold surface temperature of 80-95 degC (176-203 degF) is recommended.

Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. Minimal back pressure should be utilized to prevent glass breakage.

Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may be required.



BASF Corporation
Engineering Plastics
609 Biddle Avenue
Yandotte, MI 48192

