

Ultramid® B3WG7 BK00564

Polyamide 6



Product Description

Ultramid B3WG7 BK00564 is a 35% glass fiber reinforced, pigmented black, injection molding PA6 grade for highly rigid, dimensionally stable components which are resistant to high temperature aging and have improved retention of properties in a hot water environment.


Applications

Typical applications include automotive clutch and accelerator pedals.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm ³	1183	1.41	
Moisture, % (50% RH)	62	2	
(Saturation)		6.2	
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
23C		11,000	-
Tensile stress at break, MPa	527		
23C		188	-
Tensile strain at break, %	527		
23C		3.0	-
Flexural Modulus, MPa	178		
23C		10,000	-
IMPACT	ISO Test Method	Dry	Conditioned
Izod Notched Impact, kJ/m ²	180		
23C		12	-
Charpy Notched, kJ/m ²	179		
23C		12	-
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, C	3146	220	-
HDT A, C	75	215	-
ELECTRICAL	ISO Test Method	Dry	Conditioned
Comparative Tracking Index	IEC 60112	450	450
Volume Resistivity	IEC 60093	1E13	1E10
Dielectric Constant (1 MHz)	IEC 60250	3.9	6.2
Dissipation Factor (100 Hz)	IEC 60250	210	1,900
Dissipation Factor (1 MHz)	IEC 60250	210	1,900

Processing Guidelines

Material Handling



BASF Corporation
Engineering Plastics
609 Biddle Avenue
Ypsilanti, MI 48192

Material is supplied in sealed containers and drying prior to molding in a dehumidifying or desiccant dryer is recommended. Drying parameters are dependent upon the actual percentage of moisture in the pellets and typical pre-drying conditions are 2-4 hours at 180F (83C). Recommended moisture levels for achieving optimum surface qualities and mechanical properties is 0.05% - 0.12%. Further information concerning safe handling procedures can be obtained from the Material Safety Data Sheet (MSDS), or by contacting your BASF representative.

Typical Profile

Melt Temperature 270-295 degC (518-563 degF)

Mold Temperature 80-95 degC (176-203 degF)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

Mold Temperatures

This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics are critical, a mold surface temperature of 80-95 degC (176-203 degF) is recommended.

Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel.

Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. Minimal back pressure should be utilized to prevent glass breakage.

Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.



BASF Corporation
Engineering Plastics
609 Biddle Avenue
Yandotte, MI 48192

