

Ultramid® HFX 37

Polyamide 6



Product Description

Ultramid HFX 37 is a polyamide specialty extrusion resin combining high flexibility, excellent burst performance and outstanding chemical resistance. It offers high melt strength and enhanced heat stability.

Applications

Ultramid HFX 37 is recommended for tubing applications requiring an outstanding balance of flexibility, chemical and heat resistance and burst performance.

PHYSICAL		ISO Test Method	Property Value	
Density, g/cm		1183	1.04	
MECHANICAL		ISO Test Method	Dry	Conditioned
Tensile stress at break, MPa		527		
23C			48	-
Nominal strain at break, %		527		
23C			200	-
Flexural Modulus, MPa		178		
23C			750	-
IMPACT		ISO Test Method	Dry	Conditioned
Izod Notched Impact, kJ/m ²		180		
23C			104	-
THERMAL		ISO Test Method	Dry	Conditioned
Melting Point, C		3146	220	-

Processing Guidelines

Material Handling

Max. Water content: 0.1%

Product is supplied in sealed containers and drying prior to molding is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 65 degC (149 degF) is recommended. Drying time is dependent on moisture level, but 2-4 hours is generally sufficient. Further information concerning safe handling procedures can be obtained from the Material Safety Data Sheet. Alternatively, please contact your BASF representative.

Typical Profile

Melt Temperature 225-245 degC (437-473 degF)

Typical Barrel Profile (degC):

Rear 225-245 degC (437-473 degF)
 Middle 225-250 degC (437-482 degF)
 Front 225-245 degC (437-473 degF)

Head 230-245 degC (446-473 degF)
 Flange 230-245 degC (446-473 degF)



BASF Corporation
 Engineering Plastics
 609 Biddle Avenue
 Ypsilanti, MI 48192



Die 230-245 degC (446-473 degF)

Screw Parameters

Metering Section	40%
Transition Section	3 to 4 flights
Feed Section	balance of screw length
Compression Ratio	3.5:1 to 4.0:1
L/D Ratio	20:1 to 24:1

Tooling & Sizing

Die to Finished Tube dia. 1.5-2.0:1

Selection of pin and die size will be dependent on the material viscosity. In general, the ratio of die size to finished tube diameter is about 1.5-2.0:1. The mandrel (pin) size is determined the same way in relation to the inner tube diameter.

Free (open tank) extrusion is recommended when producing tube diameters 9.5mm and below. For larger diameters, a differential pressure vacuum tank is recommended.

Tooling draw ratio is generally higher with free extrusion versus sizing, but will depend on melt viscosity. The vacuum sizer entrance should be about 3-9% larger than the finished tube outer diameter. Selection will depend on melt viscosity and die swell of the extrudate.

Quenching

For diameters less than or equal to 9.5mm (.37") O.D., open tank quenching with normal tap water is suggested. Depending upon line speed, quenching distance can vary from 7.5 to 12 meters (24.6 -39.4 feet). A short air gap (die to quench water) is recommended for both tubing and cable jacketing for best flexibility.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.



BASF Corporation
Engineering Plastics
609 Biddle Avenue
Yandotte, MI 48192

