

Ultramid® T KR 4355 G7

BK00564

Polyamide 6/6T Copolymer



Product Description

Ultramid T KR 4355 G7 BK00564 is a 35% glass fiber reinforced injection molding PA6/6T grade featuring high toughness, stiffness, and strength, low water absorption, and high melting point (295 C). After the material has been conditioned, its mechanical properties remain stable up to 60 C. This grade is available in black.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm	1183	1.43	
Moisture, %	62		
(50% RH)		1	
(Saturation)		4.8	
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
23C		12,000	-
Tensile stress at break, MPa	527		
-40C		279	270
23C		210	200
Tensile strain at break, %	527		
23C		3	3
IMPACT	ISO Test Method	Dry	Conditioned
Charpy Notched, kJ/m ²	179		
23C		17	-
-30C		12	-
Charpy Unnotched, kJ/m ²	179		
23C		100	-
-30C		70	-
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, C	3146	295	-
HDT A, C	75	270	-
Coef. of Linear Thermal Expansion, Parallel, mm/mm C		0.15 X10-4	-
Coef. of Linear Thermal Expansion, Normal, mm/mm C		0.55 X10-4	-
ELECTRICAL	ISO Test Method	Dry	Conditioned
Comparative Tracking Index	IEC 60112	600	600
Volume Resistivity	IEC 60093	1E13	1E12
Dielectric Constant (1 MHz)	IEC 60250	4.2	4.4
Dissipation Factor (1 MHz)	IEC 60250	200	300

Note



Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

