

**Product description**

Ultramid® eXten D 458P Black is a high viscosity unfilled plasticized PA6.10 for extrusion applications. This grade is also UV stabilized. This polyamide 6,10 for extrusion is specially performing where high flexibility and toughness are requested. It is specially developed for automotive and other applications where a long term high temperature usage is requested. It is a partially bio-sourced material.

**Extrusion Notes****PROCESSING GUIDE**

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment.

Recommended maximum water content: 0,10 %

Drying conditions: 8h at 80°C with dry air, dew point -35°C

**EXTRUDER DESIGN:**

Screw type: PA type (with short transition length, 4D or less) recommended but standard type (with medium transition length, 5 to 7D) acceptable in most cases.

Screw length: Typical L/D~24-28

Screw compression rate: 3 to 4:1

Steel advice for tools: For unfilled polyamide, BASF recommends of the use of high alloy steel with a weak chromium content. For example: 35NC6 or 35CD4.

**Disclaimer**

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitutive for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and BASF SE is at their disposal to supply any additional information.

**Safety Information**

Detailed information regarding safety are available on the safety data sheet (MSDS). MSDS is sent with the first material order or available by contacting our customer services

**Regulations Compliance**

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

This grade complies with RoHS Directive 2011/65/EU, 2015/863 and local regulations as amended.

Grades produced or imported in Europe comply with REACH directive 1907/2006/EC as amended.

**Customer Services**

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design



BASF SE

67056 Ludwigshafen, Germany



# Ultramid® eXten D 458P BLACK



We create chemistry

## Product Information

Typical values for uncoloured product at 23 °C <sup>1)</sup>	Test method	Unit	Values <sup>2)</sup>
<b>General Properties</b>			
North America	-	-	+
Asia Pacific	-	-	+
South and Central America	-	-	+
Near East/Africa	-	-	+
Processing: Injection moulding (M), Extrusion (E), Blow moulding (B)	-	-	E
Colour; black (bk), uncoloured (un), coloured (co), transparent (tr)	-	-	bk
Pellets	-	-	+
<b>Physical</b>			
Water absorption, 24 h in water, 23 °C	ISO 62	%	0.46
Water absorption, equilibrium in water at 23°C	similar to ISO 62	%	1.8
Density	ISO 1183	kg/m <sup>3</sup>	1040 / -
<b>Mechanical properties</b>			
Tensile modulus	ISO 527-1/-2	MPa	850 / 600
Yield stress, 50 mm/min	ISO 527-1/-2	MPa	33 / 30
Stress at break	ISO 527-1/-2	MPa	40 / 35
Strain at break	ISO 527-1/-2	%	>200 / >200
Flexural modulus	ISO 178	MPa	690 / 470
Charpy notched impact strength ISO 179/1eA (23°C)	ISO 179/1eA	kJ/m <sup>2</sup>	100 / 120
Charpy impact strength ISO 179/1eU (23°C)	ISO 179/1eU	kJ/m <sup>2</sup>	N / N
<b>Thermal properties</b>			
HDT A (1.80 MPa)	ISO 75-1/-2	°C	51
Melting temperature, DSC (10°C/min)	ISO 11357-1/-3	°C	215
<b>Flammability</b>			
Burning Behav. at 1.6 mm nom. thickn.	IEC 60695-11-10	class	HB
Burning Behav. at thickness 0.8 mm	IEC 60695-11-10	class	HB
Burning Behav. at thickness 3.2 mm	UL-94, IEC 60695	class	HB
<b>Extrusion Notes</b>			
Extrusion cylinder temperature 1		°C	205 - 225
Extrusion cylinder temperature 2		°C	215 - 235
Extrusion cylinder temperature 3		°C	220 - 240
Extrusion, Die temperature		°C	215

### Footnotes

- 1) If product name or properties don't state otherwise.
- 2) The asterisk symbol "\*" signifies inapplicable properties.



BASF SE

67056 Ludwigshafen, Germany

