

Nydel® RC5053 BK

Polyamide 66



Product Description

Nydel RC5053 BK is a 40% glass/mineral reinforced injection molding grade containing at least 20% recycled PA66 feedstock. This product is a regional grade available in North America only.

Applications

Nydel RC5053 BK is generally recommended for applications such as automotive components (cylinder head covers), industrial housings, and parts requiring elevated temperature and dimensional stability requirements.

PHYSICAL		ISO Test Method	Property Value	
Density, g/cm		1183	1.47	
MECHANICAL		ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa		527		
23C			11,150	-
Tensile stress at break, MPa		527		
23C			130	-
Tensile strain at break, %		527		
23C			2.1	-
Flexural Modulus, MPa		178		
23C			10,400	-
IMPACT		ISO Test Method	Dry	Conditioned
Izod Notched Impact, kJ/m ²		180		
23C			6.2	-
-40C			5.3	-
Charpy Notched, kJ/m ²		179		
23C			6.4	-
THERMAL		ISO Test Method	Dry	Conditioned
Melting Point, C		3146	256	-
HDT A, C		75	217	-

Processing Guidelines

Material Handling

Max. Water content: 0.12%

Product is supplied in sealed containers and drying prior to molding is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 80 degC (176 degF) is recommended. Drying time is dependent on moisture level, but 2-4 hours is generally sufficient. Further information concerning safe handling procedures can be obtained from the Material Safety Data Sheet. Alternatively, please contact your BASF representative.


Typical Profile

Melt Temperature 280-305 degC (536-581 degF)

Mold Temperature 80-90 degC (176-194 degF)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

Mold Temperatures



A mold temperature of 80-90 degC (176-194 degF) is recommended, but temperatures of as low as 45 degC (113 degF) and as high as 105 degC (221 degF) can be used where applicable.

Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. Minimal back pressure should be utilized to prevent glass breakage.

Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.



BASF Corporation
Engineering Plastics
609 Biddle Avenue
Yandotte, MI 48192

塑料数据专家 www.ponci.com.cn/wxb/ +13538586433 +18816996168

Page 2 of 2

