

Product description

Polyamid PA66, halogen free flame retardant, reinforced with 25% of glass fibre for injection moulding. Ultramid® A 60G1 V25 Black-T is Red Phosphorous and Halogen free flame retardant grade, combines excellent all-around mechanical properties with outstanding flame retardancy and electrical performance. This product is ideally suited for industrial controls and power distribution applications such as MCBs, switches, etc. This product is available in natural and black. Specific colors can be developed upon request.

Injection Notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew Point mini -20°C. Recommended time 2-4h.

Injection Advice:

- All reinforced, flame retardant compounds generate some level of abrasion/corrosion to the steel processing equipment. These issues may be magnified by using incorrect processing conditions (temperatures, residence time, moisture level ...) during the moulding process. Therefore, BASF SE recommends you adhere to the processing conditions detailed in this technical data sheet. For equipment that comes into contact with molten flame retardant compounds, BASF SE advises you to use a steel with high chromium and high carbon content (having a minimum concentration of 16% Chromium) to prevent corrosion and abrasion. For the correct reference of steel associated to flame retardant compounds' processing, please refer to your equipment manufacturers. In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.
- The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

Disclaimer

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and BASF SE is at their disposal to supply any additional information.

Safety Information

Detailed information regarding safety are available on the safety data sheet (MSDS). MSDS is sent with the first material order or available by contacting our customer services

Regulations Compliance

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

This grade complies with RoHS Directive 2011/65/EU, 2015/863 and local regulations as amended.

Grades produced or imported in Europe comply with REACH directive 1907/2006/EC as amended.

Customer Services

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design



Product Information

Typical values for uncoloured product at 23 °C ¹⁾	Test method	Unit	Values ²⁾
General Properties			
Asia Pacific	-	-	+
Near East/Africa	-	-	+
Processing: Injection moulding (M), Extrusion (E), Blow moulding (B)	-	-	M
Colour; black (bk), uncoloured (un), coloured (co), transparent (tr)	-	-	bk,un,co
Pellets	-	-	+
Physical			
Molding shrinkage (parallel)	ISO 294-4	%	0.50
Molding shrinkage (normal)	ISO 294-4	%	0.90
Water absorption, 24 h in water, 23 °C	ISO 62	%	0.83
Density	ISO 1183	kg/m ³	1380 / -
Mechanical properties			
			dry / cond.
Tensile Strength at Break (ASTM)	ASTM D 638	MPa	125 / -
Tensile elongation at break, 2 in/min (ASTM)	ASTM D 638	%	2.8 / -
Flexural modulus (ASTM)	ASTM D 790	MPa	10300 / -
Flexural strength (ASTM)	ASTM D 790	MPa	195 / -
Izod notched impact strength ASTM D 256 (23 °C)	ASTM D 256	J/m	90 / -
Thermal properties			
HDT A (1.82 MPa), ASTM	ASTM D 648	°C	246
Melting temperature, DSC (10°C/min)	ISO 11357-1/-3	°C	262
Electrical properties			
			dry / cond.
Electric strength (d = 2.0 mm)	IEC 60243-1	kV/mm	30 / 28
Comparative tracking index, CTI, test liquid A	IEC 60112	-	600 / 600
Flammability			
Burning Behav. at 1.6 mm nom. thickn.	IEC 60695-11-10	class	V-0
Burning Behav. at thickness 0.8 mm	IEC 60695-11-10	class	V-0
Burning Behav. at thickness 3.2 mm	UL-94, IEC 60695	class	V-0
Glow Wire Flammability Index (0.8 mm)	IEC 60695-2-12	°C	960
Glow Wire Flammability Index (1.6 mm)	IEC 60695-2-12	°C	960
Glow Wire Flammability Index (3.2 mm)	IEC 60695-2-12	°C	960
Glow Wire Ignition Temperature (1.6 mm)	IEC 60695-2-13	°C	775
Glow Wire Ignition Temperature (3.2 mm)	IEC 60695-2-13	°C	775
Oxygen index	ISO 4589-1/-2	%	30
Injection			
Pre/Post-processing, Pre-drying, Temperature	-	°C	80
Pre/Post-processing, max. allowed water content	-	%	0.2
Injection molding cylinder temperature 1 (feed zone)	-	°C	260 - 275
Injection molding cylinder temperature 2 (compression)	-	°C	275 - 280
Injection molding cylinder temperature 3 (metering-zone, head room of screw)	-	°C	280 - 285
injection molding, Mold temperature, range	ISO 294	°C	60 - 90

Footnotes

1) If product name or properties don't state otherwise.

2) The asterisk symbol "*" signifies inapplicable properties.

BASF SE

67056 Ludwigshafen, Germany

