

Ultramid® A3W2G10 BK20560 **Polyamide 66**



Product Description

Ultramid A3W2G10 BK20560 is a 50% glass fiber reinforced injection molding PA66 grade.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm	1183	1.58	
RHEOLOGICAL	ISO Test Method	Dry	Conditioned
Melt Volume Rate (275 C/5 Kg), cc/10min.	1133	20	-
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
23C		15,200	-
Tensile stress at break, MPa	527		
23C		236	-
Tensile strain at break, %	527		
23C		2.9	-
Flexural Modulus, MPa	178		
23C		14,500	-
IMPACT	ISO Test Method	Dry	Conditioned
Izod Notched Impact, kJ/m ²	180		
23C		14	-
-40C		13	-
Charpy Notched, kJ/m ²	179		
23C		13	-
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, C	3146	260	-
HDT A, C	75	247	-
HDT B, C	75	256	-

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

