

# Ultradur® B 4560 BK10089

## PBT (Polybutylene Terephthalate)



### Product Description

Ultradur B 4560 BK10089 is an injection molding, pigmented black, PBT grade.

### Applications

Typical applications include industrial parts in the automotive field, such as head lamp bezels

| PHYSICAL                                    | ISO Test Method | Property Value |
|---|-----------------|----------------|
| Density, g/cm <sup>3</sup>                  | 1183            | 1.3            |
| Viscosity Number, cm <sup>3</sup> /g        | 1628            | 112            |
| Mold Shrinkage, parallel, %                 | 294-4           | 1.5            |
| Mold Shrinkage, normal, %                   | 294-4           | 2              |
| RHEOLOGICAL                                 | ISO Test Method | Property Value |
| Melt Volume Rate (250 C/2.16 Kg), cc/10min. | 1133            | 33             |
| MECHANICAL                                  | ISO Test Method | Property Value |
| Tensile Modulus, MPa                        | 527             |                |
| 23C   |                 | 2,600          |
| Tensile stress at yield, MPa                | 527             |                |
| 23C   |                 | 60             |
| Tensile strain at yield, %                  | 527             |                |
| 23C   |                 | 8              |
| Nominal strain at break, %                  | 527             |                |
| 23C   |                 | 35             |
| IMPACT                                      | ISO Test Method | Property Value |
| Charpy Notched, kJ/m <sup>2</sup>           | 179             |                |
| 23C   |                 | 3.5            |
| Charpy Unnotched, kJ/m <sup>2</sup>         | 179             |                |
| 23C   |                 | 140            |
| -30C  |                 | 85             |
| THERMAL                                     | ISO Test Method | Property Value |
| Melting Point, C                            | 3146            | 223            |
| HDT A, C                                    | 75              | 60             |

### Processing Guidelines

#### Material Handling

Max. Water content: 0.04%

To ensure optimum part performance, this product must be dried prior to molding and maintained at a moisture level of less than 0.04%. Dehumidifying or desiccant dryers operating at 100-120 degC (212-248 degF) at 4 hours drying time is recommended. Further information concerning safe handling procedures can be obtained from the Material Safety Data Sheet. Alternatively, please contact your BASF representative.

#### Typical Profile

Melt Temperature 250-270 degC (482-518 degF)

Mold Temperature 40-80 degC (104-176 degF)

Injection and Packing Pressure 35-125 bar (500-1500 psi)



BASF Corporation  
Engineering Plastics  
609 Biddle Avenue  
Ypsilanti, MI 48192



## **Mold Temperatures**

This product can be processed over mold temperatures of 40-80 degC (104-176 degF), although 80 degC (176 deg F) will result the best surface.

## **Pressures**

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. A maximum of 10 bar (145 psi) is recommended due to the risk of excessive shear.

## **Fill Rate**

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

## **Note**

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.



BASF Corporation  
Engineering Plastics  
609 Biddle Avenue  
Yandotte, MI 48192

