

Ultradur® B 6550 L

PBT (Polybutylene Terephthalate)



Product Description

Ultradur B 6550 L is a high viscosity PBT extrusion grade.

Applications

Typical applications include semi-finished products, profile and hollow rods.

PHYSICAL	ISO Test Method	Property Value
Density, g/cm	1183	1.3
Viscosity Number, cm/g	1628	160
Moisture, %	62	
(50% RH)		0.25
(Saturation)		0.5
RHEOLOGICAL	ISO Test Method	Property Value
Melt Volume Rate (250 C/2.16 Kg), cc/10min.	1133	9
MECHANICAL	ISO Test Method	Property Value
Tensile Modulus, MPa	527	
23C		2,500
Tensile stress at yield, MPa	527	
-40C		90
23C		50
Tensile strain at yield, %	527	
23C		3.5
Nominal strain at break, %	527	
23C		>50
Flexural Modulus, MPa	178	
23C		2,030
IMPACT	ISO Test Method	Property Value
Charpy Notched, kJ/m ²	179	
23C		7
Charpy Unnotched, kJ/m ²	179	
23C		N
THERMAL	ISO Test Method	Property Value
Melting Point, C	3146	223
HDT A, C	75	50
Coef. of Linear Thermal Expansion, Parallel, mm/mm C		.97 X10-4
ELECTRICAL	ISO Test Method	Property Value
Comparative Tracking Index	IEC 60112	600
Volume Resistivity	IEC 60093	>1E13
Surface Resistivity	IEC 60093	>1E15
Dielectric Constant (100 Hz)	IEC 60250	3.4
Dielectric Constant (1 MHz)	IEC 60250	3.2



Dissipation Factor (100 Hz)	IEC 60250	10
Dissipation Factor (1 MHz)	IEC 60250	221

Processing Guidelines

Material Handling

Max. Water content: 0.04%

To ensure optimum part performance, this product must be dried prior to molding and maintained at a moisture level of less than 0.04%. Dehumidifying or desiccant dryers operating at 100-120 degC (212-248 degF) at 4 hours drying time is recommended. Further information concerning safe handling procedures can be obtained from the Material Safety Data Sheet. Alternatively, please contact your BASF representative.

Typical Profile

Melt Temperature 230-290 degC (446-554 degF)

Temperature Settings (degC):

Extruder 250/240/230 degC (482/464/446 degF)

Adaptor 225 deg C (437 def F)

Die 215 deg C (419 deg F)

Screw Parameters

Metering Section	45%
Transition Section	3 to 4 flights
Feed Section	balance of screw length
Compression Ratio	3:1
L/D Ratio	20:1

Tooling & Sizing

Die to Finished Tube dia. 2.0-2.5:1 Die Gap 3-4 times the desired wall thickness

The vacuum water calibration method is recommended when producing tube diameters 8 mm and below. Water temperature should be 20 deg C (68 deg F).

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

