

Preliminary

Ultradur® S 4090 G6 LS High Speed BK15077

PBT (Polybutylene Terephthalate)



Product Description

Ultradur S 4090 G6 LS High Speed Black is a fast cycling low warpage, 30% glass filled injection molding PBT + ASA blend.

PHYSICAL	ISO Test Method	Property Value
Density, g/cm	1183	1.47
Viscosity Number, cm/g	1628	102
RHEOLOGICAL	ISO Test Method	Property Value
Melt Volume Rate (275 C/2.16 Kg), cc/10min.	1133	33.9
MECHANICAL	ISO Test Method	Property Value
Tensile Modulus, MPa	527	
23C		9,900
Tensile stress at break, MPa	527	
23C		125
Tensile strain at break, %	527	
23C		2.1
THERMAL	ISO Test Method	Property Value
Melting Point, C	3146	223
HDT A, C	75	190
HDT B, C	75	215

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.



BASF Corporation
Engineering Plastics
609 Biddle Avenue
Ypsilanti, MI 48192

