

Ultrason® P 3010

PPSU (Polyphenylsulfone)



Product Description

Ultrason P 3010 is an unfilled, flame retardant, higher viscosity injection molding PPSU grade, with improved chemical resistance.

PHYSICAL	ISO Test Method	Property Value
Density, g/cm ³	1183	1.29
Mold Shrinkage, parallel, %	294-4	0.9
Mold Shrinkage, normal, %	294-4	1
Moisture, %	62	
(50% RH)		0.6
(Saturation)		1.2
RHEOLOGICAL	ISO Test Method	Property Value
Melt Volume Rate (360 C/10 Kg), cc/10min.	1133	20
MECHANICAL	ISO Test Method	Property Value
Tensile Modulus, MPa	527	
23C		2,270
Tensile stress at yield, MPa	527	
23C		74
Tensile strain at yield, %	527	
23C		7.8
IMPACT	ISO Test Method	Property Value
Charpy Notched, kJ/m ²	179	
23C		65
-30C		24
Charpy Unnotched, kJ/m ²	179	
23C		N
-30C		N
THERMAL	ISO Test Method	Property Value
HDT A, C	75	196
Coef. of Linear Thermal Expansion, Parallel, mm/mm C		0.55 X10-4
ELECTRICAL	ISO Test Method	Property Value
Comparative Tracking Index	IEC 60112	150
Volume Resistivity	IEC 60093	>1E13
Surface Resistivity	IEC 60093	>1E14
Dielectric Constant (100 Hz)	IEC 60250	3.8
Dielectric Constant (1 MHz)	IEC 60250	3.7
Dissipation Factor (100 Hz)	IEC 60250	17
Dissipation Factor (1 MHz)	IEC 60250	89
Dielectric Strength, KV/mm	IEC 60243-1	44

Note

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.



BASF Corporation
Engineering Plastics
609 Biddle Avenue
Yandotte, MI 48192



Page 2 of 2