

# Elastollan® C75A15W

## Technical Bulletin

## Polyester Type

Elastollan® C75A15W is a polyester-based thermoplastic polyurethane (TPU) containing a plasticizer. It exhibits excellent abrasion resistance and toughness, good hydrolytic stability, good heat, oil, fuel, and solvent resistance. As with all TPU products, Elastollan® C75A15W must be dried before processing. The drying step is required to maintain a low moisture content until the product enters the processing equipment. The water content must be less than 0.03% before and processing. The typical drying conditions should be 2-4 hours @ 160°-180°F (70°-85°C). Elastollan® C75A15W can be stored for up to 1 year in its original container. Containers should be stored in a cool and dry area.

Properties	Test Method	Typical Value	
		English	SI
<b>Physical</b>			
Specific Gravity	ASTM D-792	1.17	1.17
Hardness	Shore A/D	75A	75A
<b>Mechanical</b>			
Tensile Strength (Ultimate)	psi/MPa	ASTM D-412	6100 psi 42 MPa
Tensile Stress	@100% Elong.	ASTM D-412	600 psi 4.1 MPa
Tensile Stress	@300% Elong.	ASTM D-412	1240 psi 8.6 MPa
Elongation at Break	%	ASTM D-412	770% 770%
Tensile Set at Break	%	ASTM D-412	75% 75%
Compression Set, %	22 hrs @ 23°C	ASTM D395 (B)	25% 25%
Compression Set, %	22 hrs @ 70°C	ASTM D395 (B)	40% 40%
Tear Strength	Lb./in. N/mm	ASTM D-624, Die	440 Lb./in. 77 N/mm
Taber Abrasion Resistance / mg loss	1000 gr./H-18	ASTM D-1044	50 mg 50 mg
<b>Processing Conditions, Extrusion</b>		°F/°C	340 - 375°F 170 - 190°C
<b>Processing Conditions, Inj. Molding</b>		°F/°C	345 - 375°F 70 - 190°C

The above values are shown as typical values and should not be used as specifications.  
Molded plaques 0.080" thick were cured 20 hours at 100 °C before testing

**Caution:** Contact with product dusts from regrinding operations may cause temporary irritation of the eyes and the respiratory tract. Use with local exhaust. Under hot melt processing conditions (170-230°C), wear personal protective equipment to prevent thermal burns.  
**First aid:** Eyes-Flush eyes with flowing water at least 15 minutes. If irritation develops, consult a physician. Skin-Skin contact with hot melt may cause thermal burns. Call a physician immediately. Inhalation-If vapors generated from the hot melt process are inhaled, move to fresh air. Aid in breathing. If breathing difficulties develop, see a physician immediately.  
**In case of fire:** Use water fog, foam, CO<sub>2</sub>, or dry chemical extinguishing media. Firefighters should be equipped with self-contained breathing apparatus and turnout gear.  
**Disposal:** Waste material, unused contents and empty containers must be disposed of in accordance with applicable local, state or federal regulations. Refer to our Material Safety Data Sheet for specific disposal instructions.  
**In case of chemical emergency:** Call CHEMTREC day or night for assistance and information concerning spilled material, fire, exposure and other chemical accidents.  
**Attention:** This product is sold solely for use by industrial institutions. Refer to our Material Safety Data Sheet regarding safety, usage, applications, hazards, procedures and disposal of this product. Consult your supervisor for additional information.

