

# Elastollan® C 95 A 15 HPM

®= Registered Trademark of Elastogran GmbH

## Elastogran



■ • BASF Group

### Characteristic:

Plasticizer-free, thermoplastic Polyester-Polyurethane with excellent mechanical properties and chemical resistance, outstanding wear resistance, high tear and tensile strength, good damping characteristic and high resilience performance, high heat resistance and improved setting properties.  
Processable by injection moulding and extrusion.

| Property                            | Unit              | Value       | Test method according to |
|-------------------------------------|-------------------|-------------|--------------------------|
| Hardness                            | Shore A           | <b>96</b>   | DIN 53505                |
| Density                             | g/cm <sup>3</sup> | <b>1,23</b> | DIN EN ISO 1183-1-A      |
| Tensile strength                    | MPa               | <b>49</b>   | DIN 53504-S2             |
| Elongation at break                 | %                 | <b>650</b>  | DIN 53504-S2             |
| Stress at 100 % elongation          | MPa               | <b>11,6</b> | DIN 53504-S2             |
| Stress at 300 % elongation          | MPa               | <b>15,5</b> | DIN 53504-S2             |
| Tear strength                       | N/mm              | <b>112</b>  | DIN ISO 34-1Bb           |
| Abrasion loss                       | mm <sup>3</sup>   | <b>21</b>   | DIN ISO 4649-A           |
| Compression set at room temperature | %                 | <b>20</b>   | DIN ISO 815              |
| Compression set at 70 °C            | %                 | <b>32</b>   | DIN ISO 815              |
| Compression set at 100 °C           | %                 | <b>49</b>   | DIN ISO 815              |

Test plaques are manufactured by injection moulding from pre-dried granules (water content of ≤0,02%). Test plaques are aged 20 hrs at 100°C. Specimens are cut from test plaques. Test conditions: 23°C ± 2°C and 50% ± 6% rel. humidity.

The states values are typical test results and not limiting specification values.

## General product information

# Elastollan® C 95 A 15 HPM

®= Registered Trademark of Elastogran GmbH

**Elastogran**



■ • BASF Group

### Storage and handling:

Elastollan® is hygroscopic, therefore storage in dry conditions and original container is recommended. Further information about drying, processing temperatures and post-treatment are given in our product brochure „Thermoplastic Polyurethane Elastomers (TPU) Elastollan®- Processing Recommendations“.

### Chemical Characteristics:

Polymer based on: polyurethane, stabilizing agents and additives

### Delivery form and packing:

Lentil shaped pellets

Bags, 25 kg net

Oktabins with PE liner bags, 1000 kg net

### Processing:

Processable at least for 6 months from delivery date in original sealed containers with cool dry storage.

### Hazard indication:

No particular hazards known.

Please look at the Material Safety Data Sheet before handling.

### Waste Disposal:

More detailed information is provided in our country-specific information and the Material Safety Data Sheet.

### Important Information:

There are national and international laws and regulations to consider if it is intended to produce consumer articles (e.g. articles that necessitate food or skin contact, toys etc.) or medical objects from Elastogran products. Where specific regulations do not exist, the current legal requirements of the European Union for consumer articles as well as medical products should be used as reference. Consultation with the Elastogran Sales Office and our Ecology and Product Safety Department is strongly recommended.

The data contained in this document shall constitute the agreed contractual quality of the product at the time of passing of risk. The data is reviewed at regular intervals as part of our quality assurance program. Neither this data nor the properties of product specimens shall imply any legally binding guarantee of certain properties or fitness for a specific purpose. No liability may therefore be derived from the data contained herein.