

OMNILON® PA6/6 GR20 HSL BK1000 - PA66

Physical properties	Value	Unit	Test Standard
Density	1280	kg/m ³	ISO 1183

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	7500	MPa	ISO 527-2/1A
Tensile stress at break, 5mm/min	140	MPa	ISO 527-2/1A
Tensile strain at break, 5mm/min	2.9	%	ISO 527-2/1A
Flexural modulus, 23°C	7050	MPa	ISO 178
Flexural strength, 23°C	220	MPa	ISO 178
Charpy impact strength, 23°C	6.2	kJ/m ²	ISO 179/1eU

Typical injection moulding processing conditions

Pre Drying	Value	Unit	Test Standard
Necessary low maximum residual moisture content	0.15	%	-
Drying time	4 - 8	h	-
Drying temperature	80 - 90	°C	-
Temperature	Value	Unit	Test Standard
Zone1 temperature	260 - 270	°C	-
Zone2 temperature	265 - 275	°C	-
Zone3 temperature	275 - 285	°C	-
Zone4 temperature	275 - 290	°C	-
Nozzle temperature	285 - 300	°C	-
Melt temperature	280 - 295	°C	-
Mold temperature	60 - 80	°C	-
Hot runner temperature	285 - 300	°C	-