

# Zytel® 70G30HSL BK039B

## NYLON RESIN

**ASTM D6779 PA012G30 A53480**

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® 70G30HSL BK039B is a 30% glass reinforced, heat stabilized, black nylon 66 resin for injection molding.

### Product information

Resin Identification	PA66-GF30	ISO 1043
Part Marking Code	>PA66-GF30<	ISO 11469
ISO designation	ISO 16396-PA66,GF30,M1CGHRT2,S14-100	

### Rheological properties

	dry/cond.		
Viscosity number	148 / *	cm <sup>3</sup> /g	ISO 307, 1628
Moulding shrinkage, parallel	0.3 / -	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.1 / -	%	ISO 294-4, 2577

### Typical mechanical properties

	dry/cond.		
Tensile modulus	10000 / 7000	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	190 / 120	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3 / 5	%	ISO 527-1/-2
Flexural modulus	9000 / -	MPa	ISO 178
Tensile creep modulus, 1h	* / 6800	MPa	ISO 899-1
Tensile creep modulus, 1000h	* / 5100	MPa	ISO 899-1
Charpy impact strength, 23°C	70 / 80	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	70 / 70	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	10 / 12	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	9 / 9	kJ/m <sup>2</sup>	ISO 179/1eA
Puncture - maximum force, 23°C	970 / -	N	ISO 6603-2
Puncture energy, 23°C	4.5 / -	J	ISO 6603-2
Izod notched impact strength, 23°C	10 / 12	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength, -40°C	7.0 / -	kJ/m <sup>2</sup>	ISO 180/1A
Poisson's ratio	0.34 / 0.35		

# Zytel® 70G30HSL BK039B

## NYLON RESIN

### Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	263 / *	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	75 / 20	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	250 / *	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	258 / *	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	250 / *	°C	ISO 306
Thermal conductivity, flow	0.36	W/(m K)	ISO 22007-2
Thermal conductivity of melt	0.21	W/(m K)	ISO 22007-2
Effective thermal diffusivity, flow	7E-8	m²/s	ISO 22007-4
Specific heat capacity of melt	2290	J/(kg K)	ISO 22007-4
RTI, electrical, 0.75mm	140	°C	UL 746B
RTI, electrical, 1.5mm	140	°C	UL 746B
RTI, electrical, 3.0mm	140	°C	UL 746B
RTI, impact, 0.75mm	125	°C	UL 746B
RTI, impact, 1.5mm	125	°C	UL 746B
RTI, impact, 3.0mm	125	°C	UL 746B
RTI, strength, 0.75mm	140	°C	UL 746B
RTI, strength, 1.5mm	140 / *	°C	UL 746B
RTI, strength, 3.0mm	140	°C	UL 746B

### Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 <sup>[1]</sup> / *	mm	IEC 60695-11-10
UL recognition	yes / *		UL 94
Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.4 / *	mm	IEC 60695-11-10
Oxygen index	24 / *	%	ISO 4589-1/-2
Glow Wire Flammability Index, 1.0mm	700 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 2.0mm	750 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	800 / -	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 1.0mm	725 / -	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 2.0mm	725 / -	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 3.0mm	775 / -	°C	IEC 60695-2-13
Glow Wire Temperature, No Flame, 1mm	700 / -	°C	IEC 60335-1
Glow Wire Temperature, No Flame, 2mm	700 / -	°C	IEC 60335-1
Glow Wire Temperature, No Flame, 3mm	750 / -	°C	IEC 60335-1
FMVSS Class	B		ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	22	mm/min	ISO 3795 (FMVSS 302)

[1]: and also 0.75mm

### Electrical properties

	dry/cond.		
Relative permittivity, 100Hz	4.4 / 11		IEC 62631-2-1
Relative permittivity, 1MHz	4.1 / 4.6		IEC 62631-2-1
Dissipation factor, 100Hz	70 / 4600	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	150 / 650	E-4	IEC 62631-2-1
Volume resistivity	>1E13 / 1E9	Ohm.m	IEC 62631-3-1
Surface resistivity	* / 1E13	Ohm	IEC 62631-3-2
Electric strength	38 / 32	kV/mm	IEC 60243-1

# Zytel® 70G30HSL BK039B

## NYLON RESIN

Comparative tracking index	400 / -		IEC 60112
Comparative tracking index, 23 °C	1 / -	PLC	UL 746A

### Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.9 / *	%	Sim. to ISO 62
Water absorption, 2mm	6 / *	%	Sim. to ISO 62
Density	1370 / -	kg/m <sup>3</sup>	ISO 1183
Density of melt	1200	kg/m <sup>3</sup>	

### VDA Properties

	dry/cond.		
Light stability grey scale	4		ISO 105-A02
Emission of organic compounds	10	µgC/g	VDA 277
Odour	3	class	VDA 270
Fogging, G-value (condensate)	0.6 / *	mg	ISO 6452

### Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	295 °C
Min. melt temperature	285 °C
Max. melt temperature	305 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	110 °C
Min. mould temperature	65 °C
Max. mould temperature	120 °C
Hold pressure range	50 - 100 MPa
Hold pressure time	3 s/mm
Ejection temperature	220 °C

### Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Additives	Release agent
Special characteristics	Heat stabilised or stable to heat

### Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
BMW	GS93016-PA66-GF30	(Heat Aging Resistant)
Hyundai	MS941-03 Type A-6	
Mercedes-Benz	DBL5408.45 PA66 GF30	
Mercedes-Benz	DBL5410.00 PA66 GF30	


# Zytel® 70G30HSL BK039B

## NYLON RESIN

VW Group

VW 50127 PA66-7


### Viscosity-shear rate



# Zytel® 70G30HSL BK039B

NYLON RESIN


Shearstress-shear rate



# Zytel® 70G30HSL BK039B

NYLON RESIN


Stress-strain (dry)



# Zytel® 70G30HSL BK039B

NYLON RESIN


## Stress-strain (cond.)



# Zytel® 70G30HSL BK039B

NYLON RESIN

## Secant modulus-strain (dry)






# Zytel® 70G30HSL BK039B

NYLON RESIN


## Secant modulus-strain (cond.)



# Zytel® 70G30HSL BK039B

NYLON RESIN


Stress-strain (isochronous) 140°C (cond.)



# Zytel® 70G30HSL BK039B

NYLON RESIN


Creep modulus-time 140°C (cond.)



# Zytel® 70G30HSL BK039B

NYLON RESIN


Tensile modulus-temperature (dry)



# Zytel® 70G30HSL BK039B

NYLON RESIN

Tensile modulus-temperature (cond.)



# Zytel® 70G30HSL BK039B

## NYLON RESIN

### Chemical Media Resistance

#### Acids

- ✓ Acetic Acid (5% by mass), 23°C
- ✓ Citric Acid solution (10% by mass), 23°C
- ✓ Lactic Acid (10% by mass), 23°C
- ✗ Hydrochloric Acid (36% by mass), 23°C
- ✗ Nitric Acid (40% by mass), 23°C
- ✗ Sulfuric Acid (38% by mass), 23°C
- ✗ Sulfuric Acid (5% by mass), 23°C
- ✗ Chromic Acid solution (40% by mass), 23°C

#### Bases

- ✗ Sodium Hydroxide solution (35% by mass), 23°C
- ✓ Sodium Hydroxide solution (1% by mass), 23°C
- ✓ Ammonium Hydroxide solution (10% by mass), 23°C

#### Alcohols

- ✓ Isopropyl alcohol, 23°C
- ✓ Methanol, 23°C
- ✓ Ethanol, 23°C

#### Hydrocarbons

- ✓ n-Hexane, 23°C
- ✓ Toluene, 23°C
- ✓ iso-Octane, 23°C

#### Ketones

- ✓ Acetone, 23°C

#### Ethers

- ✓ Diethyl ether, 23°C

#### Mineral oils

- ✓ SAE 10W40 multigrade motor oil, 23°C
- ✓ SAE 10W40 multigrade motor oil, 130°C
- ✓ SAE 80/90 hypoid-gear oil, 130°C
- ✓ Insulating Oil, 23°C

#### Standard Fuels

- ✓ ISO 1817 Liquid 1 - E5, 60°C
- ✓ ISO 1817 Liquid 2 - M15E4, 60°C
- ✓ ISO 1817 Liquid 3 - M3E7, 60°C
- ✓ ISO 1817 Liquid 4 - M15, 60°C
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), >90°C

#### Salt solutions

- ✓ Sodium Chloride solution (10% by mass), 23°C
- ✗ Sodium Hypochlorite solution (10% by mass), 23°C

# Zytel® 70G30HSL BK039B

## NYLON RESIN

- ✓ Sodium Carbonate solution (20% by mass), 23°C
- ✓ Sodium Carbonate solution (2% by mass), 23°C
- ✗ Zinc Chloride solution (50% by mass), 23°C

### Other

- ✓ Ethyl Acetate, 23°C
- ✗ Hydrogen peroxide, 23°C
- ✓ DOT No. 4 Brake fluid, 130°C
- ✓ Ethylene Glycol (50% by mass) in water, 108°C
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23°C
- ✓ 50% Oleic acid + 50% Olive Oil, 23°C
- ✓ Water, 23°C
- ✓ Water, 90°C
- ✗ Phenol solution (5% by mass), 23°C
- ✗ Coolant Glysantin G48, 1:1 in water, 125°C
- ✓ Urea solution (32.5% by mass), 23°C

### Symbols used:

- ✓ possibly resistant  
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).
- ✗ not recommended - see explanation  
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).