

TALCOPRENE® 1540TLT2 NERO 8134 - PP

Experimental Grade. Please contact your Celanese representative for further information.

Description

Polypropylene, homopolymer, mineral filled, high heat stabilization.

Physical properties

ISO	Value	Unit	Test Standard
Density	1270	kg/m³	ISO 1183
Melt flow rate, MFR	15	g/10min	ISO 1133
MFR temperature	230	°C	ISO 1133
MFR load	2.16	kg	ISO 1133

Mechanical properties

ISO	Value	Unit	Test Standard
Tensile modulus	3800	MPa	ISO 527-2/1A
Tensile stress at break, 5mm/min	26	MPa	ISO 527-2/1A
Flexural modulus, 23°C	3700	MPa	ISO 178
Flexural strength, 23°C	46	MPa	ISO 178
Charpy impact strength, 23°C	18	kJ/m²	ISO 179/1eU
Charpy notched impact strength, 23°C	2	kJ/m²	ISO 179/1eA

Thermal properties

ISO	Value	Unit	Test Standard
Melting point, peak	164	°C	ISO 3146
Vicat softening temperature, 50°C/h 50N	93	°C	ISO 306
Flammability @1.6mm nom. thickn.	HB	class	UL 94
Flammability at thickness h	HB	class	UL 94
thickness tested (h)	3.20	mm	UL 94

Typical injection moulding processing conditions

Pre Drying

	DryTime	DryTemp
max	3 h	100 °C
min	2 h	80 °C

Temperature

	CavTemp	MTemp	Z3Temp	Z2Temp	Z1Temp
max	60 °C	250 °C	240 °C	230 °C	210 °C
min	30 °C	230 °C	220 °C	210 °C	190 °C

Other text information

Longer pre-drying times/storage

This product should be stored in a covered facility and kept away from moisture and heat.