

# FRIANYL® XT4 GF30 V0I

PPA compound, 30% glass fiber reinforced, heat stabilized, halogens free. UL listed V0@0,4mm.

*Specifically designed for electrical and electronic applications that require high thermal, peak and continuous resistance together with compliance with the most stringent safety requirements, this compound is also easy to process with excellent aesthetic results.*

*Suitable for components that need to withstand the reflow soldering process (SMT).*

## Product information

Part Marking Code

PA6T/66-GF30 FR(40)

ISO 11469

## Rheological properties

Moulding shrinkage range, parallel

0.1 - 0.5 %

ISO 294-4, 2577

Moulding shrinkage range, normal

0.5 - 0.9 %

ISO 294-4, 2577

## Typical mechanical properties

dry/cond.

Tensile Modulus

1.58E6 /-

psi

ISO 527-1/-2

Stress at break, 5mm/min

22500 /-

psi

ISO 527-1/-2

Strain at break, 5mm/min

2.1 /-

%

ISO 527-1/-2

Charpy impact strength, 23°C

21.4 /-

ftlb/in<sup>2</sup>

ISO 179/1eU

Charpy impact strength, -30°C

19 /-

ftlb/in<sup>2</sup>

ISO 179/1eU

Charpy notched impact strength, 23°C

4.42 /-

ftlb/in<sup>2</sup>

ISO 179/1eA

Charpy notched impact strength, -30°C

4.38 /-

ftlb/in<sup>2</sup>

ISO 179/1eA

Ball indentation hardness, H 358/30

37000

psi

ISO 2039-1

## Thermal properties

Melting temperature, 10°C/min

617 °F

ISO 11357-1/-3

Temp. of deflection under load, 1.8 MPa

554 °F

ISO 75-1/-2

RTI, electrical, 0.4mm

284 °F

UL 746B

RTI, electrical, 0.75mm

284 °F

UL 746B

RTI, electrical, 1.5mm

284 °F

UL 746B

RTI, electrical, 3mm

284 °F

UL 746B

RTI, impact, 0.4mm

115 °F

UL 746B

RTI, impact, 0.75mm

239 °F

UL 746B

RTI, impact, 1.5mm

248 °F

UL 746B

RTI, impact, 3mm

257 °F

UL 746B

RTI, strength, 0.4mm

239 °F

UL 746B

RTI, strength, 0.75mm

239 °F

UL 746B

RTI, strength, 1.5mm

248 °F

UL 746B

RTI, strength, 3mm

248 °F

UL 746B

# FRIANYL® XT4 GF30 V0I

## Flammability

Burning Behav. at 1.5mm nom. thickn.	V-0 class	UL 94
Burning Behav. at thickness h	V-0 class	UL 94
Thickness tested	0.4 in	UL 94
UL recognition	yes	UL 94
Glow Wire Flammability Index, 0.75mm	1760 °F	IEC 60695-2-12
Glow Wire Flammability Index, 3mm	1760 °F	IEC 60695-2-12
Glow Wire Ignition Temperature, 0.75mm	1470 °F	IEC 60695-2-13
Glow Wire Ignition Temperature, 3mm	1610 °F	IEC 60695-2-13
FMVSS Class	SE	ISO 3795 (FMVSS 302)
Hot Wire Ignition, 0.75mm	PLC 1 s	UL 746A
Hot Wire Ignition, 1.5mm	PLC 0 s	UL 746A
Hot Wire Ignition, 3mm	PLC 0 s	UL 746A

## Electrical properties

	dry/cond.		
Volume resistivity	>1E13/-	Ohm.m	IEC 62631-3-1
Surface resistivity	>1E15/-	Ohm	IEC 62631-3-2
Electric strength	1020/-	kV/in	IEC 60243-1
Comparative tracking index	Group I		IEC 60112
Comparative tracking index	PLC 0/-	PLC	UL 746A
High Amperage Arc Ignition Resistance, 0.75 mm	PLC 2	arcs	UL 746A
High Amperage Arc Ignition Resistance, 1.5 mm	PLC 1	arcs	UL 746A
High Amperage Arc Ignition Category, 1.5 mm	PLC 1	class	UL 746A

## Other properties

Humidity absorption, 2mm	0.9 %	Sim. to ISO 62
Water absorption, 2mm	3 %	Sim. to ISO 62
Density	12 lb/gal	ISO 1183

## Characteristics

Additives	Non-halogenated/Red phosphorous free flame retardant
-----------	--

## Additional information

Injection molding	The following conditions apply to the normal injection molding process of FRIANYL XT4. Machine temperatures: barrel 310-325°C, nozzle and hot runners 325-340°C. Mold temperatures: 100°C. Back pressure: typically, < 5 bar (hydraulic pressure). Temperatures exceeding 340°C and long residence time could lead to degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please contact our technical support team.
-------------------	--

# FRIANYL® XT4 GF30 V0I

## Processing Texts

### Injection molding

The following conditions apply to the normal injection molding process of FRIANYL XT4. Machine temperatures: barrel 310-325°C, nozzle and hot runners 325-340°C. Mold temperatures: 100°C. Back pressure: typically, < 5 bar (hydraulic pressure). Temperatures exceeding 340°C and long residence time could lead to degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please contact our technical support team.

### Injection molding Preprocessing

FRIANYL XT4 compound is supplied in moisture-proof packaging. The maximum moisture content allowed for the process of injection molding is 0.10%, but to get the maximum performance and reduce possible degradation phenomena is recommended molding with a moisture content < 0.08%. The drying time depends on the initial moisture content and the drying conditions used. Typically 4-6h hours at 110°C with dry air (dew point of <-30°C) are sufficient for the material stored in unopened packs or with moisture content < 0.20-0.25%.

### Injection molding Postprocessing

Parts made by FRIANYL XT4 compound, do not change significantly their performance depending on the moisture uptake. Normally, a conditioning cycle is not necessary. After molding, with favorable environmental conditions, a piece can absorb moisture up to 0,1-0,3% in 24h and reach the equilibrium during its lifetime. The post-treatment of the parts may include annealing at 100-110°C in the oven, up to four hours. This treatment is useful to relax any internal stress.

---