

(+) 18816996168

Ponciplastics.com



---

## SOPRENE® 219N10162R NERO - SBS

---

<b>Physical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	1010	kg/m³	ISO 1183
<b>Mechanical properties (TPE)</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Tensile strain at break (TPE)	550	%	ISO 37
Tensile stress at break (TPE)	4	MPa	ISO 37
Shore A hardness, 3s	62	-	ISO 868
Tear strength	25	kN/m	ISO 34-1
Abrasion resistance	250	mm³	ISO 4649

---

### Typical injection moulding processing conditions

---

<b>Temperature</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Zone1 temperature	125 - 135	°C	-
Zone2 temperature	145 - 155	°C	-