

(+) 18816996168

Poncioplastics.com



SOPPRENE® 219N59650 NERO - SBS

| Physical properties | Value | Unit | Test Standard |
|---------------------|-------|-------------------|---------------|
| Density | 1280 | kg/m ³ | ISO 1183 |

| Mechanical properties (TPE) | Value | Unit | Test Standard |
|-------------------------------|-------|------|---------------|
| Tensile strain at break (TPE) | 380 | % | ISO 37 |
| Tensile stress at break (TPE) | 1.8 | MPa | ISO 37 |
| Shore A hardness, 3s | 50 | - | ISO 868 |
| Tear strength | 12 | kN/m | ISO 34-1 |

Typical injection moulding processing conditions

| Temperature | Value | Unit | Test Standard |
|-------------------|-----------|------|---------------|
| Zone1 temperature | 125 - 135 | °C | - |
| Zone2 temperature | 145 - 155 | °C | - |