

SOFPRENE® 540200D35/CT NEUTRO

Typical mechanical properties

Stress at 100% elongation	885 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	1000 psi	ISO 527-1/-2 or ISO 37
Stress at break	1490 psi	ISO 527-1/-2 or ISO 37
Elongation at break	580 %	ISO 527-1/-2 or ISO 37
Tear strength, parallel	331 lb/in	ISO 34-1

Other properties

Density	9 lb/gal	ISO 1183
---------	----------	----------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------