

## SOFPRENE® R700-65A - SBS

### Description

Matte, translucent and rubber-like

Physical properties	Value	Unit	Test Standard
Density	59.9	lb/ft <sup>3</sup>	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Shore A hardness-TPE, 3s	65	-	ISO 868
Abrasion resistance	200	mm <sup>3</sup>	ISO 4649

### Typical injection moulding processing conditions

Temperature	Value	Unit
Zone1 temperature	194 - 212	°F
Zone2 temperature	203 - 221	°F
Zone3 temperature	230 - 248	°F

### Other text information

### Longer pre-drying times/storage

The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

### Injection molding

Please note that the suggested temperatures are estimations. The actual desired temperatures can vary based on the molding machine design.