

SOFPRENE® SE600-50A - SBS

Description

Semi-matte, translucent and rubber-like.

Physical properties	Value	Unit	Test Standard
Density	60.6	lb/ft ³	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Shore A hardness-TPE, 3s	50	-	ISO 868
Abrasion resistance	250	mm ³	ISO 4649

Typical injection moulding processing conditions

Temperature	Value	Unit
Zone1 temperature	212 - 230	°F
Zone2 temperature	221 - 239	°F
Zone3 temperature	248 - 266	°F