

SOFPRENE® XR800-60A - SBS

Description

Super Matte, Translucent and Rubber-Like

Physical properties	Value	Unit	Test Standard
Density	59.3	lb/ft ³	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Shore A hardness-TPE, 3s	60	-	ISO 868
Abrasion resistance	230	mm ³	ISO 4649

Typical injection moulding processing conditions

Temperature	Value	Unit
Zone1 temperature	194 - 212	°F
Zone2 temperature	203 - 221	°F
Zone3 temperature	230 - 248	°F