

LAPRENE® 83GE9Z 60/3

Typical mechanical properties

Stress at break	5.5 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	680 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	60	ISO 48-4 / ISO 868

Other properties

Density	993 kg/m ³	ISO 1183
---------	-----------------------	----------

Injection

Max. mould temperature	20 - 40 °C
------------------------	------------