

LAPRENE® 8E0..D40

Typical mechanical properties

Stress at 100% elongation	5.7 MPa	ISO 527-1/-2 or ISO 37
Stress at break	14.4 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	671 %	ISO 527-1/-2 or ISO 37
Tear strength, normal	65 kN/m	ISO 34-1

Other properties

Density	1090 kg/m³	ISO 1183
---------	------------	----------

Injection

Max. mould temperature	20 - 40 °C
------------------------	------------

Processing Texts

Longer pre-drying times/storage	The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	--
