

LAPRENE® 8E3901A68

Typical mechanical properties

Stress at break	6.5 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	750 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	68	ISO 48-4 / ISO 868
Tear strength, normal	26 kN/m	ISO 34-1

Other properties

Density	1140 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Max. mould temperature	20 - 50 °C
------------------------	------------

Processing Texts

Longer pre-drying times/storage	The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	--
