

LAPRENE® 8M0..D50

Typical mechanical properties

Stress at 100% elongation	1440 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	1540 psi	ISO 527-1/-2 or ISO 37
Stress at break	2930 psi	ISO 527-1/-2 or ISO 37
Elongation at break	716 %	ISO 527-1/-2 or ISO 37
Tear strength, normal	497 lb/in	ISO 34-1

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

Processing Texts

Longer pre-drying times/storage	The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	--