

LAPRENE® 8M5..D60

Typical mechanical properties

Stress at 100% elongation	1870 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	1890 psi	ISO 527-1/-2 or ISO 37
Stress at break	3250 psi	ISO 527-1/-2 or ISO 37
Elongation at break	679 %	ISO 527-1/-2 or ISO 37
Tear strength, normal	566 lb/in	ISO 34-1

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

Processing Texts

Longer pre-drying times/storage	The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	--