

# LAPRENE® 8MC3..A55

## Typical mechanical properties

|                           |           |                        |
|---------------------------|-----------|------------------------|
| Stress at 100% elongation | 232 psi   | ISO 527-1/-2 or ISO 37 |
| Stress at 300% elongation | 363 psi   | ISO 527-1/-2 or ISO 37 |
| Stress at break           | 537 psi   | ISO 527-1/-2 or ISO 37 |
| Elongation at break       | 542 %     | ISO 527-1/-2 or ISO 37 |
| Shore A hardness, 3s      | 56        | ISO 48-4 / ISO 868     |
| Tear strength, normal     | 143 lb/in | ISO 34-1               |

## Other properties

|         |           |          |
|---------|-----------|----------|
| Density | 10 lb/gal | ISO 1183 |
|---------|-----------|----------|

## Injection

|                        |             |
|------------------------|-------------|
| Max. mould temperature | 68 - 104 °F |
|------------------------|-------------|

## Processing Texts

Longer pre-drying times/storage

The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.