

LAPRENE® 8MF3..A75

Typical mechanical properties

Stress at 100% elongation	377 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	522 psi	ISO 527-1/-2 or ISO 37
Stress at break	1460 psi	ISO 527-1/-2 or ISO 37
Elongation at break	757 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	76	ISO 48-4 / ISO 868
Tear strength, normal	223 lb/in	ISO 34-1

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

Processing Texts

Longer pre-drying times/storage	The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	--