

TECHNICAL DATA SHEET

TECHNYL 4EARTH A9E 218 C30 NC H
(Previously ECONAMID AIR 66RC30H2 NC99)

Polyamide 66, 30% carbon fiber reinforced, heat-aging stabilized, for injection moulding, natural color

General

Feature	Heat-aging stabilized
Polymer type	PA66 (Polyamide 66)
Processing technology	Injection molding
Certification	RoHS

Product identification

ISO 1043 abbreviation	PA66-CF30
ISO 16396 designation	PA66,CF30(R100),M1H,S14-220

	Condition	Standard	Unit	Value
Physical properties				
Density		ISO 1183	g/cm ³	1.27
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.15 - 0.35
Molding shrinkage, normal		ISO 294-4, 2577	%	0.5 - 0.8

Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	23000 / 15000
Stress at break	5 mm/min	ISO 527-1/-2	MPa	240 / 170
Strain at break	5 mm/min	ISO 527-1/-2	%	2.6 / 4
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	20000 / 13500
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	50 / 70
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	7.5 / 11

Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	262
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	250

Electrical properties				
Volume resistivity		IEC 62631-3-1	ohm.m	10
Surface resistivity		IEC 62631-3-1	ohm	100

TECHNICAL DATA SHEET

TECHNYL 4EARTH A9E 218 C30 NC H

	Condition	Standard	Unit	Value
--	-----------	----------	------	-------

Burning behaviour

Flammability, 0.75 mm	0.75 mm	UL 94		HB
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

Test run at 23°C if not differently specified, DAM state (dry as moulded).
*: conditioned according to ISO 1110

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	270 - 300 °C
Recommended mould temperature	80 - 110 °C

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part. Thess TECHNYL grades are not recommended for injection moulding hot runner systems with a diameter below 1mm.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.