

TECHNICAL DATA SHEET

TECHNYL 4EARTH C2E 218 V30 BK  
(Previously ECONAMID PLUS 6G30H2 BK)

Polyamide 6, 30% glass fiber reinforced, heat-aging stabilized, for injection moulding, black

General

Feature	Heat-aging stabilized		
Polymer type	PA6 (Polyamide 6)		
Processing technology	Injection molding		
Certification	RoHS	EC 1907/2006 (REACH)	
Colors available	Black		
Forms	Pellets		

Product identification

ISO 1043 abbreviation	PA6-GF30
ISO 16396 designation	PA6,GF30(R>50),M1H,S14-100

Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm <sup>3</sup>	1.37
Humidity absorption	T=23°C, 50% RH	ISO 62	%	2.2 - 2.4
Water absorption	24 hr, 23°C	ISO 62	%	1.4 - 1.5
Water absorption, saturation			%	6.2
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.3 - 0.5
Molding shrinkage, normal		ISO 294-4, 2577	%	0.8 - 1
Viscosity number	96% H2SO4	ISO 307	cm <sup>3</sup> /g	135

TECHNICAL DATA SHEET

TECHNYL 4EARTH C2E 218 V30 BK

	Condition	Standard	Unit	Value
<b>Mechanical properties</b>				<b>dam / cond.*</b>
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	9900 / 5200
Stress at break	5 mm/min	ISO 527-1/-2	MPa	145 / 85
Strain at break	5 mm/min	ISO 527-1/-2	%	2.5 / 5
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	8000 / 4600
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	220 / 140
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m²	60 / 70
Charpy impact strength, -30°C	-30°C	ISO 179/1eU	kJ/m²	50 / 50
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m²	8 / 18
Charpy notched impact strength, -30°C	-30°C	ISO 179/1eA	kJ/m²	6 / 6
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m²	55 / -
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m²	11 / 18
Izod notched impact strength, -30°C	-30°C	ISO 180/1A	kJ/m²	6 / 6

**Thermal properties**

Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	220
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	210
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	214

**Electrical properties**

Volume resistivity		IEC 62631-3-1	ohm.m	1E+013
Surface resistivity		IEC 62631-3-1	ohm	1E+014

**Burning behaviour**

Flammability, 0.75 mm	0.75 mm	UL 94		HB
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min


Test run at 23°C if not differently specified, DAM state (dry as moulded), valid for black products.  
\*: conditioned according to ISO 1110

**Processing conditions**

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	250 - 290 °C
Recommended mould temperature	80 - 100 °C

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.

Processing conditions



Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.