

TECHNICAL DATA SHEET

TECHNYL 4EARTH C2E 219 V30 BK  
(Previously ECONAMID PLUS 6G30H1 BK)

Polyamide 6, 30% glass fiber reinforced, heat-aging stabilized, for injection moulding, black

General

Feature	Heat-aging stabilized		
Polymer type	PA6 (Polyamide 6)		
Processing technology	Injection molding		
Certification	RoHS	EC 1907/2006 (REACH)	
Colors available	Black		
Forms	Pellets		

Product identification

ISO 1043 abbreviation	PA6-GF30
ISO 16396 designation	PA6,GF30(R50),M1H,S14-090

	Condition	Standard	Unit	Value
--	-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm <sup>3</sup>	1.36
Humidity absorption	T=23°C, 50% RH	ISO 62	%	2 - 2.4
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.2 - 0.4
Molding shrinkage, normal		ISO 294-4, 2577	%	0.7 - 0.9

Mechanical properties

				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	9000 / 5000
Stress at break	5 mm/min	ISO 527-1/-2	MPa	140 / 80
Strain at break	5 mm/min	ISO 527-1/-2	%	2.5 / 5
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	7500 / 4600
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	200 / 130
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m <sup>2</sup>	40 / 55
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m <sup>2</sup>	6 / 14
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m <sup>2</sup>	35 / -
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m <sup>2</sup>	5.5 / -
Rockwell hardness		ISO 2039/2	ScaleR	122 / -

TECHNICAL DATA SHEET

TECHNYL 4EARTH C2E 219 V30 BK

Condition	Standard	Unit	Value
-----------	----------	------	-------

**Thermal properties**

Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	215
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	200
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	210

**Electrical properties**

Volume resistivity		IEC 62631-3-1	ohm.m	1E+013
Surface resistivity		IEC 62631-3-1	ohm	1E+013

**Burning behaviour**

Flammability, 0.75 mm	0.75 mm	UL 94		HB
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

Test run at 23°C if not differently specified, DAM state (dry as moulded), valid for black products.  
\*: conditioned according to ISO 1110

**Processing conditions**

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	240 - 270 °C
Recommended mould temperature	90 - 100 °C

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.

**Disclaimer**

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.