

TECHNICAL DATA SHEET

TECHNYL 4EARTH C2E 238 V17 BK B
(Previously DOMONYL 1820R17T1H BK-1)

PA6, 17% Glass Fiber, Impact Modified, Heat Stabilized, Black

General

Feature	Heat-aging stabilized	Impact modified
Polymer type	PA6 (Polyamide 6)	
Processing technology	Injection molding	
Certification	RoHS	EC 1907/2006 (REACH)
Colors available	Black	
Forms	Pellets	

Product identification

ISO 1043 abbreviation	PA6-GF17
ISO 16396 designation	PA6-I,GF17(R>50),M1H,S14-050

	Condition	Standard	Unit	Value
--	-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm ³	1.22
---------	--	----------	-------------------	------

Mechanical properties

dam / cond.*

Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	5000 / -
Stress at break		ISO 527-1/-2	MPa	90 / -
Strain at break		ISO 527-1/-2	%	3 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	10 / -

Thermal properties

Melting temperature, 10°C/min		ISO 11357-1	°C	220
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	190

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1E+014
--------------------	--	---------------	-------	--------

*: conditioned according to ISO 1110

TECHNICAL DATA SHEET

TECHNYL 4EARTH C2E 238 V17 BK B

Processing conditions

Drying temperature/time	3-4hrous typical at 75-80°C
Recommended melt temperature	245 - 280 °C
Recommended mould temperature	40 - 90 °C

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.