

TECHNICAL DATA SHEET

TECHNYL A 216 NC

TECHNYL A 216 NC is an unreinforced polyamide 66, standard viscosity, for injection moulding. This grade offers all of the primary properties of unreinforced polyamide 66: thermal and mechanical properties, chemical resistance, impact and abrasion resistance.

General

Polymer type	PA66 (Polyamide 66)	
Processing technology	Injection molding	
Certification	RoHS EC 1907/2006 (REACH)	UL-Yellow Card
Applications	Connectors Industrial Applications	Consumer good application
Colors available	Black Grey	Natural Red
Forms	Pellets	

Product identification

ISO 1043 abbreviation	PA66
ISO 16396 designation	PA66,00,M1,S14-030

	Condition	Standard	Unit	Value
Physical properties				
Density		ISO 1183	g/cm ³	1.14
Humidity absorption	T=23°C, 50% RH	ISO 62	%	3.1 - 3.2
Water absorption	24 hr, 23°C	ISO 62	%	1.3
Water absorption, saturation			%	8.3
Molding shrinkage, parallel		ISO 294-4, 2577	%	1.6 - 1.7
Molding shrinkage, normal		ISO 294-4, 2577	%	1.6 - 1.7

TECHNICAL DATA SHEET

TECHNYL A 216 NC

	Condition	Standard	Unit	Value
Mechanical properties			dam / cond.*	
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	3200 / 1300
Stress at break		ISO 527-1/-2	MPa	80 / 45
Strain at break		ISO 527-1/-2	%	30 / 150
Yield stress		ISO 527-1/-2	MPa	80 / 55
Yield strain		ISO 527-1/-2	%	6 / 25
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	3300 / 1300
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	120 / 70
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m²	4.5 / 10
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m²	5 / 11


Thermal properties

Melting temperature, 10°C/min		ISO 11357-1	°C	263
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	200
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	75

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1E+013
Surface resistivity		IEC 62631-3-1	ohm	1E+015
Comparative tracking index	Solution A	IEC 60112	V	600
Dielectric strength	1 mm	IEC 60243-1	kV/mm	22

Burning behaviour


UL Yellow Card availability 	Click here to have access to the UL Yellow Card → QMFZ2.E44716			
Flammability, 1.5 mm	1.5 mm	UL 94		V2
Flammability, 3.0 mm	3.0 mm	UL 94		V2
Glow-wire flammability index, GWFI, 0.75 mm	0.75 mm	IEC 60695-2-12	°C	650
Glow-wire ignition temperature, GWIT, 1.5 mm	1.5 mm	IEC 60695-2-13	°C	650
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		<100

*: conditioned according to ISO 1110

TECHNICAL DATA SHEET
TECHNYL A 216 NC

Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	265 - 275 °C
Middle temperature	270 - 280 °C
Front temperature	280 - 285 °C
Recommended mould temperature	60 - 80 °C



Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For unfilled polyamides, Domo recommends the use of high alloy steel with a low chromium content. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.