

TECHNICAL DATA SHEET

TECHNYL AX 239S C30 NC
(Previously DOMAMID XS 66C30I2H1 119 NC99)

Polyamide 66, 30% carbon fiber reinforced, heat-aging stabilized, impact modified, for injection moulding, natural color

General

Feature	Heat-aging stabilized	Impact modified
Polymer type	PA66 (Polyamide 66)	
Processing technology	Injection molding	
Certification	RoHS	EC 1907/2006 (REACH)
Forms	Pellets	

Product identification

ISO 16396 designation	PA66-I,CF30,M1H,S14-190
-----------------------	-------------------------

	Condition	Standard	Unit	Value
--	-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm ³	1.21
---------	--	----------	-------------------	------

Mechanical properties

dam / cond.*

Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	17500 / -
Stress at break	5 mm/min	ISO 527-1/-2	MPa	165 / -
Strain at break	5 mm/min	ISO 527-1/-2	%	4.6 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	13000 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	70 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	14 / -

Thermal properties

Melting temperature, 10°C/min		ISO 11357-1	°C	262
-------------------------------	--	-------------	----	-----

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	10
Surface resistivity		IEC 62631-3-1	ohm	100

Burning behaviour

Flammability, 0.75 mm	0.75 mm	UL 94		HB
-----------------------	---------	-------	--	----

Condition	Standard	Unit	Value
-----------	----------	------	-------

Test run at 23°C if not differently specified, DAM state (dry as moulded).
*: conditioned according to ISO 1110

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	280 - 305 °C
Recommended mould temperature	70 - 100 °C

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.