

TECHNICAL DATA SHEET

TECHNYL C 116 YL 1073 LP
(Previously DOMAMID 6LV 910)

Polyamide 6, improved flowability, for injection moulding

General

Feature	Improved flowability		
Polymer type	PA6 (Polyamide 6)		
Processing technology	Injection molding		
Certification	RoHS EC 1907/2006 (REACH)	UL-Yellow Card	
Colors available	Grey		
Forms	Pellets		

Product identification

ISO 1043 abbreviation	PA6
ISO 16396 designation	PA6,M1,S12-030

Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm ³	1.17
Humidity absorption	T=23°C, 50% RH	ISO 62	%	3.3 - 3.4
Water absorption	24 hr, 23°C	ISO 62	%	1.9 - 2
Water absorption, saturation			%	9.1
Molding shrinkage, parallel		ISO 294-4, 2577	%	1.6 - 1.8
Molding shrinkage, normal		ISO 294-4, 2577	%	1.6 - 1.8
Viscosity number	96% H2SO4	ISO 307	cm ³ /g	135

TECHNICAL DATA SHEET
TECHNYL C 116 YL 1073 LP

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	3000 / -
Strain at break	50 mm/min	ISO 527-1/-2	%	25 / -
Yield stress	50 mm/min	ISO 527-1/-2	MPa	78 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	2600 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	70 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m²	5.5 / -
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m²	5 / -

Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	221

Electrical properties				
Volume resistivity		IEC 62631-3-1	ohm.m	1E+013
Surface resistivity		IEC 62631-3-1	ohm	1E+013

Burning behaviour				
UL Yellow Card availability 	Click here to have access to the UL Yellow Card → E170540-100053880			
Flammability, 0.75 mm	0.75 mm	UL 94		V2
Flammability, 1.5 mm	1.5 mm	UL 94		V2
Flammability, 3.0 mm	3.0 mm	UL 94		V2
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

Test run at 23°C if not differently specified, DAM state (dry as moulded), valid for natural colored products.
*: conditioned according to ISO 1110

Processing conditions	
Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Suggested max moisture	0.2 %
Rear temperature	230 - 235 °C
Middle temperature	235 - 240 °C
Front temperature	235 - 245 °C
Recommended melt temperature	230 - 245 °C
Recommended mould temperature	60 - 80 °C

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.