

TECHNICAL DATA SHEET

TECHNYL C 118 MX30 BK  
(Previously DOMAMID 6LVT30H2 BK)

Polyamide 6, 30% mineral filler, heat-aging stabilized, improved flowability, for injection moulding, black

General

Feature	Heat-aging stabilized	Improved flowability
Polymer type	PA6 (Polyamide 6)	
Processing technology	Injection molding	
Certification	RoHS	

Product identification

ISO 1043 abbreviation	PA6-MD30
ISO 16396 designation	PA6,MD30,M1H,S12-060

Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm <sup>3</sup>	1.38
Humidity absorption	T=23°C, 50% RH	ISO 62	%	2.1
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.6 - 0.8
Molding shrinkage, normal		ISO 294-4, 2577	%	0.6 - 0.8
Melt volume-flow rate, MVR, 5.0 kg	275°C, 5kg	ISO 1133	cm <sup>3</sup> /10 min	50

Mechanical properties

				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	6400 / 4200
Stress at break	50 mm/min	ISO 527-1/-2	MPa	70 / 35
Strain at break	50 mm/min	ISO 527-1/-2	%	3 / 4
Yield stress	50 mm/min	ISO 527-1/-2	MPa	70 / 35
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	6000 / 2800
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m <sup>2</sup>	30 / 23
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m <sup>2</sup>	3 / 7

TECHNICAL DATA SHEET

TECHNYL C 118 MX30 BK

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	190
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	125

Test run at 23°C if not differently specified, DAM state (dry as moulded).  
\*: conditioned according to ISO 1110

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	240 - 280 °C
Recommended mould temperature	60 - 80 °C

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.