

TECHNICAL DATA SHEET

TECHNYL C 216 V50 BK Z

(Previously DOMAMID 6LVG50 300 BK)

Polyamide 6, 50% glass fiber reinforced, improved flowability, for injection moulding, black

TECHNYL C 216 V50 BK Z is a polyamide 6, reinforced with 50% of glass fibre, for injection moulding. This grade offers high mechanical strength, high surface aspect by easy flow & low pressure moulding for injection moulding.

General

Feature	Improved flowability High stiffness	High dimensional stability
Polymer type	PA6 (Polyamide 6)	
Processing technology	Injection molding	
Certification	RoHS	EC 1907/2006 (REACH)
Applications	Automotive Applications Industrial Applications	Consumer good application
Colors available	Black	
Forms	Pellets	

Product identification

ISO 1043 abbreviation	PA6-GF50
ISO 16396 designation	PA6,GF50,M1,S12-160

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm ³	1.56
Humidity absorption	T=23°C, 50% RH	ISO 62	%	2.2 - 2.4
Water absorption	24 hr, 23°C	ISO 62	%	1.4 - 1.5
Water absorption, saturation			%	6.2
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.15 - 0.35
Molding shrinkage, normal		ISO 294-4, 2577	%	0.75 - 0.95
Melt volume-flow rate, MVR, 5.0 kg	275°C, 5kg	ISO 1133	cm ³ /10 min	30
Viscosity number	96% H ₂ SO ₄	ISO 307	cm ³ /g	125

TECHNICAL DATA SHEET

TECHNYL C 216 V50 BK Z

	Condition	Standard	Unit	Value dam / cond.*
Mechanical properties				
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	16500 / 10500
Stress at break	5 mm/min	ISO 527-1/-2	MPa	220 / 135
Strain at break	5 mm/min	ISO 527-1/-2	%	2.5 / 5.5
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	15000 / 9000
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	330 / 220
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m²	90 / 110
Charpy impact strength, -30°C	-30°C	ISO 179/1eU	kJ/m²	85 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m²	15 / 20
Charpy notched impact strength, -30°C	-30°C	ISO 179/1eA	kJ/m²	12 / 13

Thermal properties

Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	220
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	210
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	215

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1E+013
Surface resistivity		IEC 62631-3-1	ohm	1E+014

Test run at 23°C if not differently specified, DAM state (dry as moulded).
*: conditioned according to ISO 1110

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Suggested max moisture	0.2 %
Rear temperature	235 - 240 °C
Middle temperature	240 - 250 °C
Front temperature	250 - 260 °C
Recommended melt temperature	235 - 260 °C
Recommended mould temperature	60 - 90 °C

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufacturers in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.